

Davco



Product Data Sheet

Rejuvenation Grout



A ready to use grout designed to be applied straight over existing grout



FEATURES & BENEFITS

- Ready to use
- Suitable for use in pools
- Easy and fast application
- Stain, mould and bacteria resistant

PACKAGING

Available in a 1.7kg pail

AVAILABLE COLOURS



Picket Fence



Platinum



Thunderbolt



Antique Lace



Fossil



Abyss

WHERE TO USE

Surfaces

Most common substrates.

Tiles

Suitable for glossy and smooth tiles only. Grout joints with at least 1mm of depth from the existing grout surface to the top of the tile.

Note: Do not use on flush joints or highly textured and / or porous tiles.

Areas

Suitable for interior and exterior applications. Commercial and domestic walls and floors including pools and submerged areas.

PRODUCT INFORMATION

VOC Content

Low VOC - 2g/L (SCAQMD method 304-91)

Coverage

1.7kg pail of Davco Rejuvenation Grout covers approximately 20m² (based on 200 x 200mm tiles with a 4mm wide by 1mm deep grout joint)

Curing Time

Dry area 12 hours

Wet area 48 hours

Submerged area 7 days



MADE IN AUSTRALIA



DIRECTIONS FOR USE

- Test the grout in an inconspicuous area first
- You will need a firm but flexible grout float or squeegee, a large tiler's sponge and a bucket of clean water
- Plan the area to be grouted, you should only grout up to 1m² at a time
- Start by working backwards out of corners

SURFACE PREPARATION

- All surfaces must be installed according to manufacturer's instructions and relevant Australian Standard(s) and be structurally sound, dry, clean and free from movement, oil, grease, wax, sealers, curing compounds, release agents and any other loose or contaminating material
- The tile and grout surface must be thoroughly cleaned with either a mild soap and water mixture or sugar soap mixture. If required, a bristle brush can be used to clean the existing grout joints
- Rinse surface with clean water to ensure there is no residue on the surface and allow the surface to completely dry prior to application of Rejuvenation Grout

APPLICATION

1. Stir thoroughly before use. Apply to the grout joint and using the float or squeegee, spread diagonally across the joint. Ensure you are filling the joint evenly. Only cover 1m² at a time as Rejuvenation Grout will be difficult to clean off once it dries.
2. After approximately 5-10 minutes, clean off excess grout and evenly shape the grout joints by laying a damp sponge on the tile surface and lightly wiping in a circular motion.
3. Finish the application with a single diagonal wipe to the tile surface with a well wrung sponge. Avoid applying excessive force or repeatedly wiping as this may remove the grout from the joint. If the water in the bucket becomes dirty, replace with clean water.

Clean-up & Return to Service

- After the grout sets (approx. 30 minutes), some grout haze may still remain on the tiles. With clean water and a very well wrung sponge, wipe the tile surface in a circular, buffing motion, avoiding the grout joints

PRECAUTIONS

Safety

- SDS is available from www.davcoaustralia.com.au
- It is recommended that applicators wear PVC or similar gloves and safety goggles while handling this product
- Keep out of reach of children. If eye contact occurs, rinse with cool water. If ingested get immediate medical assistance

General

- Do not apply in temperatures above 35°C or below 5°C
- In cool and / or humid conditions, allow longer setting times

Specific

- Rejuvenation Grout is not recommended for use on highly textured or porous tiles due to its high bond strength
- Existing grout must be at least 1mm below the surface of the tile, allowing sufficient depth for the Rejuvenation Grout to bond to the grout joint
- Alternatively rake out sufficient grout to allow 1mm depth
- Do not allow the Rejuvenation Grout to skin / dry out in the tub. Always replace the plastic film after use
- Do not use acidic cleaners on Rejuvenation Grout
- When used in pools the pH of the water must remain between 6 and 8
- For other uses not mentioned in these instructions, please contact Sika Australia

TECHNICAL DATA

TECHNICAL DATA	REJUVENATION GROUT
Appearance	Coloured paste
Curing time before return to dry area service	12 hours
Curing time before return to wet area service	48 hours
Curing time before return to submerged area service	7 days
Shelf life when stored unopened in elevated, cool, dry location	12 months

All measurements are taken at 22°C and 50% relative humidity. Specifications vary according to site conditions and should be taken as a guide only.



Quality
ISO 9001



Davco products manufactured in Australia are produced in accordance with quality management systems certified as complying with AS/NZS ISO 9001:2008.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Ltd

55 Elizabeth Street, Wetherill Park NSW 2164 | 1300 22 33 48 | aus.sika.com

The use of this product is beyond the manufacturer's control, and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. All workmanship must be carried out in accordance with AS 3958.1-1991. The information contained herein is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for a particular application. Users are asked to check that the literature in their possession is the latest issue.