

PRODUCT DATA SHEET

Vapordiffuser/V

Plastomeric bituminous roof membrane with adhesive spots for use on damp substrates

DESCRIPTION

Vapordiffuser/V is an APP modified bituminous roof membrane which is torch applied, flexible at -10 °C and reinforced with a glass fleece. The underside has spots of a special elastomeric heat adhesive compound, which is activated during torch application. The membrane bonding area is approximately 35% which allows the diffusion of residual moisture from damp substrates.

USES

Roof waterproofing membrane for:

- Flat and slope roofs under protective layers or ballast
- Balconies and terraces under a heavy protection layer i.e. tiles, gravel etc.
- A first layer on damp substrates or old bitumen coverings

CHARACTERISTICS / ADVANTAGES

- Weight: ~4,0 kg/m²
- Good flexibility at -10 °C
- Vapour diffuser and waterproofing incorporated in the same membrane
- Adhesive strips reduce the strain from cyclic movement across the laying substrate
- Good mechanical properties (tensile, tear)
- Easy to install by torching method
- Choice of primers to suit substrate and weather conditions
- Can be applied onto concrete substrates and over existing bitumen roofing membranes

APPROVALS / CERTIFICATES

- CE marking and Declaration of Performance to EN 13707 - Reinforced bitumen sheets for roof waterproofing

PRODUCT INFORMATION

Product declaration	EN 13707: Reinforced bitumen sheets for roof waterproofing		
Composition	APP modified bitumen		
Reinforcing material	Glass fleece		
Packaging	Roll size		
	Length	7,50 m	
	Width	1,00 m	
Shelf life	36 months from date of production		
Storage conditions	Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.		
Appearance and colour	Top surface	Polyethylene film	
	Backing	35 % adhesive spots covered by polyethylene film	
Length	7,5 m -1 %		
Width	1 m -1 %		
Tensile strength	Longitudinal	300 N/50 mm ± 20 %	(EN 12311-1)
	Transversal	200 N/50 mm ± 20 %	
Elongation	Longitudinal	2 % ± 1 %	(EN 12311-1)
	Transversal	2 % ± 1 %	
Tear strength	Longitudinal	70 N ± 30 %	(EN 12310-1)
	Transversal	70 N ± 30 %	
Flexibility at low temperature	≤ -10 °C	(EN 1109)	
Watertightness	60 kPa	(EN 1928-Method B)	
External fire performance	F roof	(EN 13501-5)	
Reaction to fire	Class E	(EN 13501-1)	
Ambient air temperature	+5 °C min. / +50 °C max.		
Relative air humidity	80 % max.		
Substrate temperature	+5 °C min. / +50 °C max.		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- On sloping roofs with a gradient more than 40% and / or high wind areas, the application must be integrated with mechanical fixing at the ends of the sheets. Contact Sika Technical Services for additional information.
- At low temperatures, take care unrolling to avoid damaging the membrane.
- Use suitable footwear to avoid puncturing the membrane.
- Do not apply to wet, or unclean surfaces.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at +260 °C) will be damaged making the membrane un-useable.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps. If this occurs, un-bonded areas must be lifted and re-torched.
- If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

SUBSTRATE QUALITY

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up. Complete roof system must be designed and secured against wind uplift loadings. The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loosely adhering particles.

SUBSTRATE PREPARATION

Use the appropriate preparation equipment to achieve the required substrate quality.

APPLICATION METHOD / TOOLS

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Priming

Apply the appropriate primer from the Index Indexver range, at the correct consumption to the prepared dry surface and allow to dry before next application stage. Refer to the individual Product Data Sheets.

Alignment

Unroll, align and re-roll correctly before torching.

Overlaps

Side: 100mm. End: 150 mm.

Fastening

Vapordiffuser/V can be mechanically fixed on the substrate by using the correct type of fasteners. Contact Sika Technical Services for additional information.

Torching

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the backing film starts to melt, the membrane is ready to stick. Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

Detailing

All details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc.

must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for torch-applied membranes.

Protection

The membrane must be protected from damage during any ongoing site activities.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited
ABN 12 601 342 329
61, Smith Street
Sydney, NSW 1585

Product Data Sheet
Vapordiffuser/V
April 2023, Version 01.02
020920011990000231

VapordiffuserV-en-AU-(04-2023)-1-2.pdf