

## PRODUCT DATA SHEET

# Sikalastic® WPU

Elastomeric, single component, fibre reinforced, water based polyurethane membrane

### DESCRIPTION

- Sikalastic® WPU is a premixed, single component, water based polyurethane waterproofing membrane.
- Sikalastic® WPU is a Class III membrane with high extensibility and forms an elastomeric, seamless waterproofing membrane for use in internal and external applications for under tiled finishes including shower recesses, bathrooms, laundries, decks, balconies, podiums and rooftops.
- Sikalastic® WPU has low VOC and adheres to a wide variety of substrates.
- Sikalastic® WPU contains micro fibre reinforcement for improved tensile strength and crack bridging capabilities.

### USES

- Concrete
- Sand/cement screeds
- Cement Render
- Fibrous cement sheeting
- Compressed fibrous cement sheeting
- Water resistant plasterboard

### PRODUCT INFORMATION

<b>Packaging</b>	15 Litre Pail
<b>Colour</b>	Grey
<b>Shelf life</b>	12 months from date of manufacture in original, sealed containers, if the storage conditions are met.
<b>Storage conditions</b>	Store in dry, weatherproof environment, protected from direct sunlight at temperatures between +5°C and +25°C
<b>Volatile organic compound (VOC) content</b>	43Grams/Litre- Low VOC (SCAQMD method 304-91)
<b>Tensile strength</b>	2.52 MPa
<b>Permeability to water vapour</b>	~ 3.29g/m <sup>2</sup> /24hr

### FEATURES

- High Extensibility >300% (Class III)
- UV Stable
- Micro fibre enhanced reinforcement
- Internal and external applications
- Single component- no mixing, ready to use
- Water based- Low VOC, Non-hazardous
- Compatible with Sika® tile adhesives

### CERTIFICATES AND TEST REPORTS

AS 4858-2004: Wet Area Membranes  
 BRANZ Appraisal- Interior applications  
 BRANZ Appraisal- Exterior applications

## APPLICATION INFORMATION

Consumption	10m <sup>2</sup> per 15Ltr Pail (1mm Dry Film Thickness)
Layer thickness	2x coats of 750 Micron (Wet film) to achieve a DFT of 1mm
Waiting time to overcoating	Allow Sikalastic® WPU 2-3 hours to dry between coats. Allow longer in adverse weather conditions.
Drying time	Allow a minimum of 10 hours curing prior to applying finished covering, and a minimum of 3 days to cure before flood testing. Flood testing is dependent on site specific conditions and may require longer cure times than 3 days, please ensure material is well cured before proceeding.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

### LIMITATIONS

- Sikalastic® WPU is not suitable for negative hydrostatic head of water pressure.
- Sikalastic® WPU must not be applied over damp or wet substrates.
- Sikalastic® WPU must not be applied in rain or if bad weather is imminent.
- Sikalastic® WPU must not be applied over coatings or contaminations.
- Sikalastic® WPU must be applied at the recommended coverage rate.
- Sikalastic® WPU must not be used in submerged applications.
- Sikalastic® WPU must not be used as a trafficable coating.
- Do not apply Sikalastic® WPU when the temperature is below 5°C or greater than 35°C.
- Do not allow Sikalastic® WPU to freeze.
- To eliminate contamination or damage, the finished covering must be applied as soon as Sikalastic® WPU has cured.
- Timber floors must be overlaid with suitable cement sheeting prior to waterproofing.
- Contact Sika® Technical Services for advice if further information is required

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

All surfaces to be waterproofed must be firm, clean, dry, structurally sound and smooth. All grease, oil, wax, curing compounds, dust, loose material, laitance and other contaminants must be removed. All projections and rough spots should be dressed off to achieve

a level surface. The substrate surface must be continuous and provide falls to waste as per National AS3740-2021 and AS4654.2-2012.

### Priming

Substrate	Primer
Porous substrates	Davco Ultraprime Davco PrimeX SikaTile 010 Secure Prime
Dense Concrete	Davco PrimeX
Early aged screed	Sikalastic Moisture Seal
Metal & PVC flanges	SikaTile 015 Prep n Prime

### Concrete

Allow at least 28 days for the concrete to cure. Concrete should be left with an open surface. All traces of curing compounds or sealers should be removed prior to application. Old concrete must be thoroughly cleaned and washed and allowed to dry. The surface should be even unless falls are incorporated where required, imperfections to be repaired with a suitable Sika® MonoTop repair mortar.

### Sand / Cement Screeds and Renders

The screeds and / or renders must conform to the appropriate standard and should be left with a wood float finish and left to cure for at least 7 days. Moisture content should be below 4% before membrane application.

### Building Boards

Water resistant plasterboard and fibrous cement sheeting must be solidly fixed in accordance with the manufacturer's instructions specifically for tiling.

### Non Porous Substrates

It may be necessary to mechanically prepare the area. Any existing tiles must be well bonded and be free from any sealers or coatings. Dense, low absorbent and impervious surfaces must be primed with SikaTile 015 Prep 'N' Prime. Confirm adhesion and compatibility of the primer to the substrate before proceeding with membrane application.

### Static Crack & Sheet Joint Treatment

For static cracks 0.5 – 3mm wide rout out and clean thoroughly before filling with Sika® Neutral Cure silicone to form a Bond Breaker, for all sheet joints and seams clean thoroughly and fill with Sika® Neutral Cure silicone to form a Bond Breaker. For dynamic cracks, expansion joints and control joints contact Sika® technical service for advice.

### Bond Breaker / Connector sealant

Suitable bond breaker: Any Sika neutral cure silicone sealant

Suitable connector sealant: SikaFlex Fillet or SikaFlex Construction AP

Sikalastic® WPU is a Class III membrane with high extensibility and is designed for use with a 12mm annulus bond breaker at floor/wall and wall/wall junctions. A bond breaker must be installed at areas subject to movement, wall/wall junction, wall/floor junction, sheet joints and seams, penetrations and where there is a change in the direction or substrate type.

## CLEANING OF EQUIPMENT

Clean tools and equipment with clean water while the material is still wet. Cured coating can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

### Product Data Sheet

Sikalastic® WPU

March 2025, Version 01.04

02179020220000013

SikalasticWPU-en-AU-(03-2025)-1-4.pdf