

PRODUCT DATA SHEET

Sika AnchorFix®-3+

High-performance, 2-component epoxy anchoring adhesive

DESCRIPTION

Solvent-free, thixotropic, 2-component, epoxy resin-based, high performance anchoring adhesive.

USES

Sika AnchorFix®-3+ may only be used by experienced professionals.

For the fixing of non-expanding anchors in the following:

Structural work:

- Rebar / steel reinforcement anchoring in new and refurbishment works
- Threaded rods
- Bolts and special fastening / fixing systems
- Mechanical and electrical services installation (heating and ventilating, sanitary, etc)
- Anchoring of supports for ducting and equipment

Metalwork, carpentry:

- Fixing of handrails, balustrades and supports
- Fixing of railings
- Fixing of window and door frames

In the following substrates:

- Concrete
- Hollow and solid masonry
- Steel
- Wood
- Hard natural and reconstituted stone*
- Solid rock*

* These substrates may vary greatly, in particular with regard to strength, composition and porosity. Therefore, for each application the suitability of Sika AnchorFix®-3+ Adhesive must be tested by first applying the Product only to a sample area. Check in particular bond strength, surface staining and discoloration.

CHARACTERISTICS / ADVANTAGES

- Long Open Time
- Can be used in damp concrete
- High load capacity
- ETA to ETAG 001 for anchoring in concrete
- Non-sag, even overhead
- Styrene-free
- Shrinkage-free hardening
- Standard guns can be used (with the 250ml cartridge)
- Low odour
- Low wastage

APPROVALS / CERTIFICATES

- Bonded injection type anchor according to ETAG 001 Part 1 and 5 Option 7, ETA-14/0125, Declaration of Performance and provided with the CE marking.
- Anchoring product for reinforcing steel bar according to EN 1504-6:2006, Declaration of Performance 0204030100300000021001, certified by notified factory production control certification body 0921, certificate of conformity of the factory production control 0921-CPD-2056, and provided with the CE marking.
- Tested according to NF/AFNOR standard P 18-831

PRODUCT INFORMATION

Packaging	250 ml standard cartridge	12 cartridges per box pallet: 75 boxes
Colour	Component A	clear / translucent
	Component B	grey
	Component A+B mixed	light grey
Shelf life	12 months from date of production All Sika AnchorFix®-3+ cartridges have the expiry date printed on the label.	
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight.	
Density	Component A	~1.18 kg/l
	Component B	~1.71 kg/l
	Component A+B mixed	~1.45 kg/l

TECHNICAL INFORMATION

Compressive strength	Curing time	+5 °C	+23 °C	+40 °C	(ASTM D 695-96)
	16 hours	~11 N/mm ²	~94 N/mm ²	~108 N/mm ²	
	1 day	~17 N/mm ²	~104 N/mm ²	~115 N/mm ²	
	3 days	~86 N/mm ²	~112 N/mm ²	~123 N/mm ²	
	7 days	~89 N/mm ²	~114 N/mm ²	~127 N/mm ²	
Pull-out resistance	Ultimate load	> 70 kN*			(NF P 18-822)
	Slippage	< 0.6 mm			
	* Maximum load of the testing machine Test parameters for anchoring of rebar in slabs:				
	Steel quality	B500B			
	Rebar diameter	12 mm			
	Drill hole diameter	22 mm			
	Anchoring depth	120 mm			
Service temperature	Long term	-40 °C min. / +50°C			(ETAG 001, Part 5)
	Short term (1–2 hours)	+50 °C			

APPLICATION INFORMATION

Mixing ratio	Component A : component B = 1 : 1 by volume
Layer thickness	5 mm max.
Sag flow	Non-sag, even overhead
Product temperature	Sika AnchorFix®-3+ must be at a temperature of between +5 °C and +30 °C for application.
Ambient air temperature	0 °C min. / +40 °C max.
Dew point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.
Substrate temperature	0 °C min. / +40 °C max.

Curing time

Temperature	Open time - T _{gel}	Curing time - T _{cur} *
+35 °C – +40 °C	10 minutes	7 hours
+20 °C – +35 °C	15 minutes	14 hours
+10 °C – +20 °C	35 minutes	30 hours
+5 °C – +10 °C	75 minutes	45 hours

Minimum cartridge temperature: +5 °C

* In wet concrete the curing time must be doubled.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Mortar and concrete must be at the required strength.

No need to be 28 days old.

Substrate strength (concrete, masonry, natural stone) must be verified.

Pull-out tests must be carried out if the substrate strength is unknown.


The anchor hole must always be clean, dry, free from oil and grease etc.

Loose particles must be removed from the holes.


Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.

MIXING


Getting the cartridge ready: 250 ml




1. Unscrew the cap



2. Pull out the plug




3. Screw on the static mixer




4. Place the cartridge into the gun and start application

APPLICATION METHOD / TOOLS

Anchors in solid masonry/concrete



Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.



The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)


Important: use oil-free compressors.



Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.




Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer. In any case avoid entrapping air. For deep holes extension tubing can be used.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.

Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be removed mechanically.

FURTHER INFORMATION

For specific information on design refer to the separate documentation provided:

Technical Documentation Sika AnchorFix®-3+ 870 43 08

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48



Product Data Sheet

Sika AnchorFix®-3+

September 2020, Version 01.02

020205010030000002

SikaAnchorFix-3+-en-AU-(09-2020)-1-2.pdf