

PRODUCT DATA SHEET

Sikafloor®-08 Primer

CONCENTRATED ACRYLIC PRIMER FOR FLOORING & TILING SYSTEMS

DESCRIPTION

Sikafloor®-08 Primer is a versatile & economical priming concentrate.

When diluted 1:2 or 1:3 with water = 15L or 20L of mixed priming liquid. This consistency is used for priming porous concrete surfaces.

Alternatively Sikafloor®-08 Primer can be applied neat on suitably prepared timber/wood or cement sheeting substrates prior to Sikafloor®-4020 Fiber-Level.

USES

Applied in combination with self-levelling compounds from Sikafloor® or Lanko® ranges.

Sikafloor®-08 Primer:

- Can be applied on interior or exterior concrete surfaces.
- Can be used in residential, commercial and industrial applications
- Can be applied on floors and walls where required

PRODUCT INFORMATION

Composition	Acrylic liquid
Packaging	5L plastic bottle
Shelf life	12 months from date of production (in closed packaging)
Storage conditions	Store in a cool, dry place. Do not store below +5 °C. Material that has been mixed with water should be used within a week.

CHARACTERISTICS / ADVANTAGES

- Fast drying
- Solvent free
- Can be applied over various substrates - concrete, timber/wood, cement sheeting
- Great penetration into porous construction materials
- Non-combustible
- Suitable for internal or external applications

APPROVALS / CERTIFICATES

Green Star VOC-SCQMD Rule 1168

SYSTEM INFORMATION

System structure	When Sikafloor® or Lanko® self-levelling products are applied	
	Porous concrete	Timber/wood/cement sheeting
	Sikafloor®-08 Primer (diluted)	Sikafloor®-08 Primer (neat)
	Sikafloor® or Lanko® self-levelling materials	Sikafloor®-4020 FiberLevel
	Chosen flooring	Chosen flooring
Substrates	<ul style="list-style-type: none"> ▪ Internal or external porous concrete ▪ Internal cement levelling compound ▪ Internal Sikafloor®-4020 FiberLevel levelling compound ▪ Internal timber/wood/cement sheeting/wall lining 	
Mixing ratio	Surface	Dilution & application
	Normal steel trowel concrete	1:3
	CSP 1 - CSP 2	x 1 coat (broom or roller applied)
	Mechanically prepared concrete	1:3
	CSP 3 - CSP 10	x 2 coats (broom applied)
	Cement levelling compound	1:3
		x 1 coat (broom applied)
	Sikafloor®-4020 FiberLevel	No dilution, apply neat
		x 1 coat (roller applied)
	Timber/wood/cement sheeting/wall lining	No dilution, apply neat
	x 1 coat (roller applied)	
	<p>Note: Mix ratio & application device recommendations should be followed depending on the type of surface mentioned above. Not following these recommendations may result in poor performance and possible product/system failure.</p>	
Consumption	<ul style="list-style-type: none"> ▪ 1:3 dilution ~ 6-9 m2 per mixed L ▪ Neat ~ 5-6 m2 per L <p>Average consumption is dependent on absorbency of the substrate, applicator device and mixing ratio.</p>	
Substrate temperature	Between +5 °C to 35 °C	
Waiting time to overcoating	Before applying Sikafloor® or Lanko® products.	
	Substrate	Waiting time
	Porous concrete	~10 - 20 min @ 23 °C
		Per coat
	Cement levelling compound	~10 - 20 min @ 23 °C
		Per coat
	Sikafloor®-4020 FiberLevel	~120 min @ 23 °C
	Per coat	
Timber/wood/cement sheeting/wall lining	~120 min @ 23 °C	
	Per coat	
	Note: All values are approximate and subject to climatic conditions.	

BASIS OF PRODUCT DATA

Manufactured in Australia.

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

temperatures below 5°C and above 35°C.

- Sikafloor®-08 Primer is not recommended as a trafficable seal coat over cement based materials.
- Directions for Sikafloor®-08 Primer installation must be followed for best product performance.
- Clean tools and equipment with warm water and detergent while the product is still wet.

IMPORTANT CONSIDERATIONS

- Do not apply Sikafloor®-08 Primer in fully submerged situation - pools/ponds.
- Do not mix or apply Sikafloor®-08 Primer in

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Suitable mixing buckets, clean cool water, mixing drill & paddle.
Soft bristle broom or 12+mm napped paint roller.

SUBSTRATE QUALITY / PRE-TREATMENT

- All substrates should be fully cured, structurally sound, clean, dry, and free of surface contaminants. Concrete substrate must be fully cured at least 28 days old with a pull off strength of 1.5 MPa.
- Cement-based substrates must be porous and accept water penetration. Test porosity by lightly sprinkling water on various areas of the substrate. If water penetrates, then a good bond with Sikafloor®-08 Primer can be achieved. If water beads and fails to be absorbed, surface contaminants are most likely present and a loss of adhesion may occur.
- Surface contaminants that are present should be mechanically removed before installation of Sikafloor®-08 Primer.
- All substrates must be free of efflorescence and not subject to hydrostatic pressure. If the cement-based substrate has efflorescence or high moisture (RH), Sikafloor®-158 W Fast Barrier + moisture barrier system should be considered.
- Timber/wood/cement sheeting/Sikafloor®-4020 FiberLevel must be free of any previous coatings. The manufacturers installation guidelines must be followed when timber/wood/cement sheeting are first installed. Movement of sub-floors must be minimized by mechanical or chemical procedures prior to the installation of Sikafloor® products.
- Please refer also to the product data sheets of subsequent suitable materials for further details.

APPLICATION

▪ APPLY DILUTED

Sikafloor®-08 Primer by way of a soft bristle broom, or 12+mm napped roller. Correct amount of mixed primer liquid should always be applied to the prepared substrate, giving good penetration and film build. Thin applications may result in pinholing in the finished surface or debonding levelling compound from the substrate.

On particularly porous surfaces where the initial prime coat is absorbed immediately, or mechanically prepared surfaces a second coat is recommended. Avoid foam during application by adding more liquid.

▪ APPLY NEAT

Sikafloor®-08 Primer over raw timber/chipboard, cement sheeting or Sikafloor®-4020 FiberLevel with a long napped roller 12mm+.

Note:

For best practice it is recommended subsequent construction materials are applied as soon as primer is dry, but no later than 24hrs.

- Care must be taken not to allow dust to settle on the freshly primed surface.
- If dust has contaminated the surface, first vacuum clean and apply another coat of primer before subsequent materials are installed.
- Do not allow primer to pool while drying as this will cause a soft spot under construction material.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48



Product Data Sheet

Sikafloor®-08 Primer

July 2021, Version 01.03

020815120010000119

Sikafloor-08Primer-en-AU-(07-2021)-1-3.pdf