

PRODUCT DATA SHEET

PROHESIVE® ECOFLEX

A FLEXIBLE RUBBER MODIFIED, POLYMER FORTIFIED, CEMENT BASED ADHESIVE DESIGNED FOR A VARIETY OF TILING APPLICATIONS

DESCRIPTION

PROHESIVE® ECOFLEX is a flexible, rubber modified, polymer fortified, cement based adhesive designed for a variety of tiling applications. PROHESIVE® ECOFLEX has extended coverage and is suitable for internal and external applications.

USES

PROHESIVE® ECOFLEX

Is suitable for thin & thick bed application.
Is suitable for wall & floor tiling applications
Is suitable for internal and external tiling applications

SUITABLE TILE TYPES ARE;

Ceramic Tiles
Porcelain tiles
Mosaic Tiles
Natural Stone - non moisture sensitive
Terracotta
Quarry Tiles

SUITABLE SUBSTRATES INCLUDE;

Concrete (concrete above 35Mpa requires mechanical preparation prior to fixing)
Compressed Cement Boards*
Ceramic tile Underlay / Fibre cement boards*
CMU Blockwork & Brickwork
Sika approved waterproof membranes
Cement mortar beds / Screeds
Gypsum Plasterboard*

*refer to board manufacturers instructions for further details and load limits.

CHARACTERISTICS / ADVANTAGES

- Great workability
- Extended coverage
- Flexible S1 Performance
- Internal & External use
- Wall & Floor use
- Suitable over early age screeds / mortar beds
- Suitable for under tile heating systems
- Suitable over a variety of substrates
- Low VOC

APPROVALS / CERTIFICATES

VOC Content: 5g/L (SCAQMD method 304-91)

PRODUCT INFORMATION

Composition	Cement, Rubber crumb, Quartz minerals, Polymers, & special additives.
Packaging	20kg Bags / 64 Pags per Pallet
Appearance / Colour	Off white powder with rubber crumb.
Shelf life	12 Months from date of manufacture.
Storage conditions	Store off ground in dry cool conditions for maximum shelf life (high humidity will reduce shelf life).
Density	1.4kg/Litre
Product declaration	C1ES1 Class adhesive AS ISO 13007.1

APPLICATION INFORMATION

Mixing ratio	7 Litres of water per 20kg Bag	
Consumption	Notched Trowel Size	Approx coverage per Bag
	6mm Notched Trowel	12m ²
	10mm Notched Trowel	8m ²
	Consumption is dependant on surface profile, roughness and application technique.	
Ambient air temperature	+5°C Min / +35°C max	
Substrate temperature	+5°C Min / +35°C Max	
Pot Life	1.5 Hours at 23°C & 50% RH	
Open Time	30 Minitues at 23°C & 50% RH	
Adjustability time	15 Minutes at 23°C & 50% RH	
Applied product ready for use	USE	WAIT TIME
	Grouting on walls	6 hours
	Grouting on floors	6-8 Hours
	Light Foot Traffic	16 hours
	Full service	5 -7 Days
	Values determined at laboratory cconditions: 23°C & 50% RH. Higher temperatures will reduce times and lower temperatures with in-crease times.	

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- Substrate deflection, all substrate under loads must not exceed L/360 for tiles & L/450 for stone.
- Substrates must be properly cured, structurally sound, free from friable particles, clean, dry, and free from contaminants such as dirt, dust, oil, grease, curing compounds, crystalline admixtures, release agents, laitance or efflorescence.
- Dependant on the substrate condition and contamination to be removed from the surface, perform adequate preparation techniques, such as water blasting, scarification, or blast cleaning in order to remove all traces of contaminants that could reduce the products adhesion to the substrate.
- For tiling wet areas, a suitable Sika under tile waterproof membrane should be used prior to tiling.

CONCRETE FLOORS: Allow 28 days for concrete to cure. Concrete shall be left with open surface - steel trowel finishes are generally acceptable if they accept water. Wood float finishes are preferred where possible.

CEMENT MORTAR BEDS / SCREEDS: Must be installed as per AS ISO 3958.1-2007.

SHEETED / BOARD SUBSTRATES: All boards and sheets must be installed as per manufacturers instructions and specifically designed for tiling.

PRIMING:

Porous substrates: Eco Prime WB*

Non Porous Substrates: Eco Prep n Prime*

** refer to primer datasheet for addition information*

MIXING

Pour clean cool water into a mixing container and gradually pour the the PROHESIVE® ECOFLEX powder into the container and stir with a slow speed mixing drill (approx 500RPM). Mix for 2-3 minutes to a smooth lump free homogenous consistency. Allow the product to stand (slake) for 5 minutes then restir for an additional minute. Do not add more water. Restirring the mixture may be required during the adhesives pot life.

APPLICATION

Tiles shall be fixed in accordance to with AS 3958.1-2007.

- Ensure the backs of tiles are clean and free from dust and contaminants.
- Apply the adhesive to the substrate with the appropriate sized notched trowel to achieve coverage requirement on both substrate and the back of the tile. Tiles may require back-buttering to achieve minimum coverage requirements.
- Apply the adhesive with a notched trowel in a single direction. Apply the tile, while pressing into the wet adhesive, break the ridges with the tile to fully bed the tile into the adhesive.
- It is advisable to periodically check the backs of the tiles for adhesive coverage requirements as per the AS3958.1-2007.

- Only apply as much adhesive that can be covered prior to adhesive skinning. If skinning occurs remove and replace with fresh adhesive.
- Remove any excess adhesive from the face of the tile with a damp sponge and ensure grout joint are of uniform depth.
- Movement, expansion and control joints must be installed as per AS 3958.1-2007.
- For tile over tile applications, existing tiling must be adequately cleaned prior to application. Ensure existing tiling is sound and free from defect. Prime existing tiles with Prep n Prime and allow to dry. Gloss or polished tiles must be mechanically prepared prior to priming with Eco Prep n Prime.

CLEANING OF EQUIPMENT

Adhesive can be cleaned off tools and equipment with water while wet.

IMPORTANT CONSIDERATIONS

- PROHESIVE® ECOFLEX is not suitable for applications directly over tongue and groved timber flooring, plywood, medium density fibre board, or masonite. Cement boards shall be installed as per manufacturers specification prior.
- PROHESIVE® ECOFLEX is not suitable for moisture sensitive stone.
- Mechanical fixing is recommended when fixing externally above 3 meters.
- PROHESIVE® ECOFLEX is not suitable to be applied directly over solvent based waterproof membranes.
- When using externally and in wet areas ensure falls to wastes and adequate and correct.
- The performance of cement based adhesives will be compromised when used above 35°C and under 5°C.
- Efflorescence is beyond the control of the manufacturer and is influence by external factors.
- PROHESIVE® ECOFLEX is not suitable for submersed applications.
- Contact Sika Australia for advise if further information is required.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48



Product Data Sheet

PROHESIVE® ECOFLEX

October 2020, Version 01.03

02171010200000221

PROHESIVECOFLEX-en-AU-(10-2020)-1-3.pdf

