

PRODUCT DATA SHEET

SikaBond® SprayFix

Multipurpose, high performance, aerosol spray adhesive

DESCRIPTION

SikaBond® SprayFix is a multipurpose, high performance, aerosol spray adhesive which can be used for both temporary and permanent bonding applications.

USES

Typical applications include:

- Upholstery
- Floor and other repairs
- Furniture lamination
- Art and craft work (e.g. mounting prints)

SikaBond® -SprayFix can be used on many substrates, including:

- Felts and fabrics
- Metals
- Foams
- Cork
- Most plastics
- Rubber gaskets
- Fibreglass
- Wood e.g. plywood, particle board

CHARACTERISTICS / ADVANTAGES

- Easy to use
- Low odour
- Dries clear
- Fast drying time (approximately 2-4 minutes)
- High initial strength
- Contains no chlorinated solvents suitable for indoor use
- Repositionable for 1-2 minutes
- Versatile bonds well to many substrates

PRODUCT INFORMATION

Composition	Synthetic polymer
Packaging	150g, 350g
Shelf life	2 years if storage conditions are met
Storage conditions	Must be stored in original, undamaged packaging, in dry conditions and out of direct sunlight, at temperatures between +10°C and +25°C.
Colour	White (clear when dry)
Ambient air temperature	+10°C - +40°C

Product Data Sheet

SikaBond® SprayFix April 2023, Version 02.02 02051303000000094

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

Sika Australia Pty Limited

ABN 12 001 342 329 aus.sika.com Tel: 1300 22 33 48

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The surface must be clean, dry and free of dust, grease and oils.

APPLICATION METHOD / TOOLS

Shake can well before use.

Spray from a distance of about 20-30 cm, using a sweeping motion to get an even coverage of adhesive. For temporary or low strength permanent bonding, apply to only one surface. For high strength, permanent bonding, apply adhesive to both surfaces. Allow the adhesive to become tacky before firmly pressing the surfaces together, applying even pressure along the entire bonding surface. Pressing the surfaces together either while the adhesive is still wet or after it has lost its tack will produce a weak bond – the optimum time for bonding is when the adhesive is dry but still tacky. Bonded materials may be repositioned within 1-2 minutes to ensure correct surface alignment.

CLEANING OF EQUIPMENT

After use, the spray tip should be flushed by turning the can upside down and pressing the tip until clear propellant comes out. Uncured overspray may be removed with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaBondSprayFix-en-AU-(04-2023)-2-2.pdf

