

# Davco



## Product Data Sheet

# Sanitized<sup>®</sup> Tile & Grout Sealer



A solvent-based sealer that helps protect against stains, soiling,



## FEATURES & BENEFITS

- Clear solution which cures to an invisible, water repellent coating
- Easy to apply

## PACKAGING

Available in a 500ml can

## WHERE TO USE

### Surfaces

Only suitable for cement-based grouts. Can also be used over most unglazed porous ceramic tiles.

### Areas

Suitable for interior and exterior applications. Commercial and domestic walls and floor grout joints.

## PRODUCT INFORMATION

### Coverage

Davco Sanitized<sup>®</sup> Tile & Grout Sealer approximately 6-10m<sup>2</sup>/L (depending upon surface porosity and site conditions)

### Drying Time

24 hours at 22°C



MADE IN  
AUSTRALIA



## PRECAUTIONS

### Safety

- SDS is available from [www.davcoaustralia.com.au](http://www.davcoaustralia.com.au)

### Specific

- Do not flood the floor with Sanitized® Tile & Grout Sealer. Apply only in small sections and clean up the area before moving on
- Do not allow excess sealer to dry on the surface of the tiles as it will leave a white residue
- For other uses not mentioned in these instructions, please visit [www.davcoaustralia.com.au](http://www.davcoaustralia.com.au)

## DIRECTIONS FOR USE

- Test product in an inconspicuous area first

## SURFACE PREPARATION

- Ensure grout joints and tile surfaces are thoroughly dry, clean, free from dirt, dust, grease, oil, wax and other contaminants

## APPLICATION

1. Apply using a sponge, brush or spray gun.
2. Allow 5-10 minutes for the sealer to penetrate the surface, then wipe off excess with a damp sponge.
3. Allow the sealer to cure for 24 hours prior to putting the area in use.

Note: If only sealing grout joints of porous ceramic or terracotta tiles, ensure clean up method is pre-tested. It may be necessary to mask the joints

## Clean-up & Return to Service

- Excess Sanitized® Tile & Grout Sealer and tools can be cleaned up with mineral turps while the product is still wet

TECHNICAL DATA	TILE & GROUT SEALER
Appearance	Clear liquid
Coverage based on surface porosity and site conditions	6-10m <sup>2</sup> /L
Specific gravity	1.0kg/L
Drying time	24 hours
Shelf life when stored unopened in elevated, cool, dry location	12 months

All measurements are taken at 22°C and 50% relative humidity. Specifications vary according to site conditions and should be taken as a guide only.



Davco products manufactured in Australia are produced in accordance with quality management systems certified as complying with AS/NZS ISO 9001:2008.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Ltd

55 Elizabeth Street, Wetherill Park NSW 2164 | 1300 22 33 48 | [aus.sika.com](http://aus.sika.com)

The use of this product is beyond the manufacturer's control, and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. All workmanship must be carried out in accordance with AS 3958.1-1991. The information contained herein is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of the product for a particular application. Users are asked to check that the literature in their possession is the latest issue.