

PRODUCT DATA SHEET

Sika® FerroGard®-901 S

Corrosion inhibiting concrete admixture

DESCRIPTION

Sika® FerroGard®-901 S is a liquid concrete admixture based on Sika® FerroGard® technology for use in reinforced concrete and mortar. It acts as a corrosion inhibitor for the steel reinforcement. By using Sika® FerroGard®-901 S, the life expectancy and durability of reinforced concrete can be substantially increased.

USES

Sika® FerroGard®-901 S is designed for reinforced concrete particularly at risk of corrosion. It specifically provides protection from chloride-induced corrosion.

Typical uses are in:

- Concrete roads
- Bridges
- Tunnels
- Retaining walls
- Industrial plants
- Multi storey car parks

CHARACTERISTICS / ADVANTAGES

By using Sika® FerroGard®-901 S both the anodic and cathodic reactions of the electrochemical corrosion process are reduced. The product forms a protective layer on the steel surface which delays the onset of corrosion and also reduces the corrosion rate.

Sika® FerroGard®-901 S is a combination of organic corrosion inhibitors.

The following advantages can be achieved using Sika® FerroGard®-901 S:

- Corrosion protection for embedded reinforcing steel, especially from chloride attack
- Protection from the destructive influences of reinforcement corrosion
- No negative influences on the properties of both the fresh and the hardened concrete

PRODUCT INFORMATION

Composition	Amino alcohols
Packaging	IBC 1000 litre bulk deliveries
Shelf life	12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.
Storage conditions	Storage at temperatures between 1 °C and 35 °C. Protect from direct sunlight, frost and contamination.
Appearance and colour	Green liquid
Density	~1.05 kg/L
pH-Value	~9.5 at +20 °C

TECHNICAL INFORMATION

Concreting guidance

The standard rules of good concreting practice, concerning production and placing, are to be followed.

Laboratory trials shall be carried out before concreting on site, especially when using a new mix design or producing new concrete components.

Fresh concrete must be cured properly and curing applied as early as possible.

Specific advice

Frozen Sika® FerroGard®-901 S can be used after slow thawing at room temperature, followed by intense stirring.

APPLICATION INFORMATION

Recommended dosage

12 kg/m³

Dispensing

Sika® FerroGard®-901 S is mixed with the gauging water or added at the same time into the concrete mixer. It may also be added to the concrete in the transit mixer at the point of discharge. In this case, an additional mixing time of at least 1 minute per m³ concrete must be observed. Before discharging it, check the concrete visually for uniform consistency.

The quantity of Sika® FerroGard®-901 S in the mix design should be taken into consideration when determining the quantity of water for a specific w/c-ratio.

Compatibility

Sika® FerroGard®-901 S can be combined with many other Sika products.

Note:

Always conduct trials before combining products in specific mixes and contact Sika® technical service for more information and advice.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

There are no local restrictions

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

SikaFerroGard-901S-en-AU-(04-2023)-1-2.pdf

Product Data Sheet

Sika® FerroGard®-901 S

April 2023, Version 01.02

02140305100000011