

PRODUCT DATA SHEET

SikaInject®-315 PS

(formerly TPH.® POLINIT)

Polymeric strengthening (PS) compound for SikaInject® Acrylate Resins

DESCRIPTION

SikaInject-315 PS is a polymeric strengthening compound for the acrylate resin SikaInject-304 DE. PS compound is used instead of water for preparation of component B.

Use with further SikaInject-3** acrylate resins on request.

USES

SikaInject®-315 PS may only be used by experienced professionals.

- Sealing of cracks, joints and cavities in concrete, masonry or in the ground
- Sealing of all types of leaking building components in damp or water saturated ground
- Filling/sealing of annular gaps in tunneling or shaft structures
- Repair of waterproofing membranes e.g. in tunnels or basements
- Repair of expansion joints e.g. failed waterbars
- Curtain Injection

FEATURES

- Permanently elastic
 - watertight up to 7 bar
 - Increase of flexibility
 - Increase of adhesion on siliceous surfaces
 - Reduction of shrinkage in case of ventilation
 - CE-certified (EN 1504-5)
 - Resistant to alternating freeze and thaw exposure
- Once cured, the product is insoluble in water and hydrocarbons and resistant to alkalis

CERTIFICATES AND TEST REPORTS

CE-Mark, DOP, concrete injection for (S) filling of cracks, joints, honeycombs acc. to EN 1504-5
Renovation of defective expansion joints; MFPA Leipzig
Resistance test to freeze-thaw cycling; MFPA Leipzig
Resistance test to concrete-corrosive fluids; MFPA Leipzig
Watertightness-Test 7 bar, acc. to DIN EN 14068; MFPA Leipzig
Tested with SikaInject®-304 DE

PRODUCT INFORMATION

Packaging	1000 kg IBC
Colour	white, liquid
Shelf life	12 months in original packaging
Storage conditions	dry, between 15-25°C, protected from heat, frost and direct sunlight
Density	~1.01 kg/l (DIN EN ISO 3675)
Viscosity	8 - 15 mPas (DIN EN ISO 2555)

TECHNICAL INFORMATION

Modulus of elasticity in flexure	~ 0.49 MPa (DIN EN ISO 527) with SikalInject®-304 DE
Tensile strength	~ 0.16 MPa (DIN EN ISO 527) with SikalInject®-304 DE
Water absorption	~ 40 % (DIN EN ISO 62) with SikalInject®-304 DE
Elongation at break	~ 710 % (DIN EN ISO 527) with SikalInject®-304 DE

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

SikalInject®-315 PS can also be used in combination with other SikalInject®-3** acrylate resins. Reaction and performance data can be found in the respective product data sheet.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheets (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

SikalInject®-315 PS is used instead of water for preparing component B of SikalInject®-304 DE. At least 3 minutes of mixing are required for dissolving the part B (salt). The component B prepared in this way is ready-for-use and remains stable for ~ 5 hours (depending on temperature). The product is pumped in a mixing ratio of 1 : 1 (parts by volume, A : B) using a 2-component injection pump.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited
 ABN 12 001 342 329
 aus.sika.com
 Tel: 1300 22 33 48