

## PRODUCT DATA SHEET

# Sikafloor®-304 W

2-part PUR matt seal coat part of the Sika Comfortfloor® flooring range

### DESCRIPTION

Sikafloor®-304 W is a two part water based, very low VOC, polyurethane, matt seal coat.

### USES

Sikafloor®-304 W may only be used by experienced professionals.

Matt seal coat for Sika ComfortFloor® flooring range

### CHARACTERISTICS / ADVANTAGES

- Water based
- Very low odour
- Good UV and yellowing resistance
- Easy to clean

### SUSTAINABILITY

- Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings
- VOC Emission certificate according to AgBB und DIBt approval requirements (AgBB – Committee for Health-related Evaluation of Building Products, DiBt – German Institute for Building Technology), Eurofins report No. 770027B

### APPROVALS / CERTIFICATES

- Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 01 04 005 0 000002 1041, certified by notified factory production control certification body 0620, and provided with the CE marking.
- Coating for surface protection of concrete according to EN 1504-2:2004, Declaration of Performance 02 08 01 04 005 0 000002 1041, certified by notified factory production control certification body 0620, and provided with the CE marking.
- Fire classification acc. to EN 13501-1 Report No. KB-Hoch-090971, Test institute Hoch, Germany.
- Biological resistance certificate Sikafloor-304W CSM Statement of Qualification - ISO 846, very good - Report No. SI 1108-533 Fraunhofer IPA, Germany

### PRODUCT INFORMATION

<b>Composition</b>	PUR	
<b>Packaging</b>	Part A	6.0 kg containers
	Part B	1.5 kg containers
	Part A+B	7.5 kg ready to mix units
<b>Shelf life</b>	Part A:	6 months from date of production
	Part B:	12 months from date of production
<b>Storage conditions</b>	The product must be stored properly in original, unopened and undam-	

aged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.

<b>Appearance and colour</b>	Resin - part A	white, liquid	
	Hardener - part B	yellowish, liquid	
Sikafloor®-304W is matt after final curing.			
<b>Density</b>	Part A	~ 1.05 kg/l	(DIN EN ISO 2811-1)
	Part B	~ 1.13 kg/l	
	Mixed resin	~ 1.07 kg/l (diluted with 5 % Water)	
	All Density values at +23°C		

## TECHNICAL INFORMATION

<b>Gloss level</b>	<b>Angle</b>	<b>Value</b>	(ISO 2813)
	85°	< 55	
	60°	< 10	
<b>Chemical resistance</b>	Resistant to many chemicals. Contact Sika technical service for specific information.		

## SYSTEM INFORMATION

<b>Systems</b>	Please refer to the System Data Sheet of: <b>Sikafloor MultiFlex® PS-32 UV</b> Seamless, smooth, low voc, elastic, polyurethane floor covering with optional colour flakes		
----------------	---	--	--

## APPLICATION INFORMATION

<b>Mixing ratio</b>	Part A : part B = 80 : 20 (by weight)		
<b>Consumption</b>	~0.13 kg/m <sup>2</sup> /layer These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level and wastage etc.		
<b>Ambient air temperature</b>	+10 °C min. / +30 °C max.		
<b>Relative air humidity</b>	75 % max. During curing the humidity should not exceed 75 % max. Adequate fresh air ventilation must be provided to remove the excess moisture from the curing product.		
<b>Dew point</b>	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.		
<b>Substrate temperature</b>	+10 °C min. / +30 °C max.		
<b>Pot Life</b>	<b>Temperature</b>	<b>Time</b>	
	+10 °C	~ 50 minutes	
	+20 °C	~ 30 minutes	
	+30 °C	~ 20 minutes	
Caution: End of potlife is not noticeable.			
<b>Curing time</b>	Before overcoating Sikafloor®-304 W allow:		
	<b>Substrate temperature</b>	<b>Minimum</b>	<b>Maximum</b>
	+10 °C	26 hours	4 days
	+20 °C	16 hours	3 days
	+30 °C	12 hours	2 days

Based on relative humidity of max. 70 % and good ventilation. Times are

approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Applied product ready for use	Temperature	Foot traffic	Light traffic	Full cure
	+10 °C	~ 30 hours	~ 48 hours	~ 6 days
	+20 °C	~ 16 hours	~ 24 hours	~ 4 days
	+30 °C	~ 12 hours	~ 18 hours	~ 3 days

Note: Times are approximate and will be affected by changing ambient conditions

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

### Substrate Quality & Preparation

Please refer to Sika Method Statement: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

### Application Instructions

Please refer to Sika Method Statement: "MIXING & APPLICATION OF FLOORING SYSTEMS".

### Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

## IMPORTANT CONSIDERATIONS

- Freshly applied Sikafloor®-304 W must be protected from damp, condensation and water for at least 7 days (+20 °C).
- Unevenness of substrates as well as inclusions of dirt cannot be covered by thin sealers coats. Therefore substrate and adjacent areas must be cleaned thoroughly prior to application.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## DIRECTIVE 2004/42/CE LIMITATION OF EMISSIONS OF VOC

According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type wb) is 140 g/l (Limit 2010) for the ready to use product.

The maximum content of Sikafloor®-304 W is < 140 g/l VOC for the ready to use product.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull off strength shall not be less than 1.5 N/mm<sup>2</sup>. If in doubt apply a test area first.

### MIXING

Prior to mixing, stir part A mechanically. When all of part B has been added to part A, mix continuously for 3 minutes until a uniform mix has been achieved. During the mixing of the Components A and B add 5–7 % clean water. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. After mixing give the material a rest for 10 minutes. Over mixing must be avoided to minimise air entrainment.

### Mixing Tools:

Sikafloor®-304 W must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

### APPLICATION

Prior to application, confirm substrate moisture content, relative humidity and dew point. Uniformly spread Sikafloor®-304 W by using a short pile nylon roller. Sikafloor®-304 W can also be applied by using a airless spray equipment. A seamless finish can be achieved if a "wet" edge is maintained during application.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Australia Pty Limited**

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

**Product Data Sheet**

Sikafloor®-304 W

April 2023, Version 04.01

020812060030000001

