

PRODUCT DATA SHEET

Sika® Filler-101

Ready to use water based fine surface and joint filler

DESCRIPTION

Sika® Filler-101 is a water based, ready to use joint filling and wide spreading of internal surfaces

USES

- Sika® Filler-101 is suitable for indoor filling work on plaster boards, fabrics, old wallpapers, etc.
- Sika® Filler-101 has a very smooth finish
- Sika® Filler-101 complies with EN 15824 "Specifications for external and internal plasters based on organic binders" and EN 13963 "Jointing materials for gypsum plasterboards" Type 3A (ready-mix, dual-purpose compound)

CHARACTERISTICS / ADVANTAGES

- Ready to use, no mixing required
- Easy application
- High initial tack or grab on plaster and concrete
- Quick drying

APPROVALS / CERTIFICATES

- Internal plaster based on organic binder according to EN 15824, DoP 02 03 04 02 001 0 000016 1084; ITT performed by external laboratory 0402; System 3 certification and provided with the CE-mark
- Jointing materials for gypsum plasterboards Type 3A (Ready-mix, dual purpose compound) according to EN 13963, DoP 02 03 04 02 001 0 000016 1084; System 4 certification and provided with the CE-mark

PRODUCT INFORMATION

Composition	Filled styrene-acrylate dispersion.
Packaging	250 ml plastic tube 400 ml plastic tube 5 Ltr plastic pail
Shelf life	12 months from date of production if stored properly in undamaged and unopened original sealed packaging.
Storage conditions	Store in cool and dry conditions. Protect from frost.
Appearance and colour	White paste
Maximum grain size	D _{max} : 0.12 mm
Density	~1.200 kg/l

APPLICATION INFORMATION

Consumption	Depends on the substrate roughness and thickness of the layer applied. As a guide, ~ 1 l of Sika® Filler-101 can fill ~ 1 m² per mm thick.
Layer thickness	3 mm max.

Product Data Sheet

Sika® Filler-101April 2023, Version 01.02
02184030300000010

Ambient air temperature	+5°C min. / +35°C max.
Substrate temperature	+5°C min. / +35°C max.
Waiting time to overcoating	~4 hours

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Clean, free from dust, dry and oil.

MIXING

Sika® Filler-101 is supplied ready to use - no mixing is required.

APPLICATION

Sika® Filler-101 can be applied with spatula in layer thicknesses from 0 - 3 mm.

When filling deeper holes or cracks the filler must be applied in several layers and must be allowed to almost dry. Holes and cracks from 4 - 15 mm can more easily be filled with Sika® Filler-105. When dried finish the surface with Sika® Filler-101.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

Sika Australia Pty Limited

ABN 12 001 342 329 aus.sika.com Tel: 1300 22 33 48

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaFiller-101-en-AU-(04-2023)-1-2.pdf

