

# PRODUCT DATA SHEET

# Sika Retarder® N

Re- Set Retarder

#### **DESCRIPTION**

Sika Retarder® N is used to retard the setting time of the concrete to allow concreting under conditions of high ambient temperatures and placing of mass concrete. It is designed to be used for pumped, prestressed and structural concrete.

#### **USES**

- Increases the setting time of concrete
- Used in high temperatures
- Excellent for large concrete pours

#### **FEATURES**

- Minimises the risk of cold joints.
- After the initial retardation, the rate of hardening proceeds at a rate equivalent to, or greater than, unretarded normal concrete.
- Delivery of concrete can be made over long distances from the premix concrete plant.

### **CERTIFICATES AND TEST REPORTS**

Sika Retarder® N meets and exceeds all requirements of Australian Standard 1478.1-2000 for Set-Retarding Admixture (Re)

#### PRODUCT INFORMATION

Composition	Aqueous solution of selected carbohydrates
Packaging	Bulk deliveries 1000 litre IBC 205 litre drum 10 litre container
Shelf life	Stored at temperatures between 5°C and 35°C in unopened original containers protected from direct sunlight and frost, shelf life is at least one (1) year.
Storage conditions	Store at temperature between $5^{\circ}\text{C}$ and $35^{\circ}\text{C}$ , protected from the direct sunlight
Appearance and colour	Cloudy yellow liquid
Specific gravity	1.05 g/cm³ approx.
Concreting guidance	Concrete should be placed according to good concrete practice and proper curing procedures should take place
Specific advice	May slightly increase air content when used with water reducers.
Recommended dosage	The effect of Sika Retarder® N depends on a number of factors such as cement type, ambient temperature and mix design. The optimum dosage should be determined by site or laboratory tests with the particular concrete mix design.

**Product Data Sheet** 

Sika Retarder® N

September 2024, Version 01.04 021406011000000051

	The rate of addition is generally in the range of: $200  \text{ml} \pm 100  \text{ml}$ per $100  \text{kg}$ of cementitious materials. Note: For dose rates higher than $400  \text{ml}/100  \text{kg}$ please refer to your Sika representative.
Compatibility	Sika Retarder® N is compatible with all the types of Portland cement . When using with other admixtures, check their compatibility first.

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### **IMPORTANT CONSIDERATIONS**

Increase in dosage rate will cause an increase in the setting time. If this occurs, do not change to an accelerator. A severe overdose may delay the setting time of the concrete to detrimental extent.

# **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

# **LOCAL RESTRICTIONS**

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329 aus.sika.com Tel: 1300 22 33 48

Sika®