

PRODUCT DATA SHEET

Sikafloor®-350 N Elastic

DESCRIPTION

Sikafloor®-350 N Elastic is a two part, solvent free, highly elastic polyurethane resin.

USES

Sikafloor®-350 N Elastic may only be used by experienced professionals.

Sikafloor®-350 N Elastic is used for:

- Highly elastic, crack-bridging, trafficable, slip resistant wearing layers
- Particularly suitable for car park decks, garage floors and bridges etc.

CHARACTERISTICS / ADVANTAGES

- Very good crack-bridging ability even at low temperatures (down to -20°C)
- Mechanically resistant as a broadcast system
- Watertight
- Economical in use
- Solvent free

PRODUCT INFORMATION

Composition	Polyurethane	
Packaging	Part A	9.0 kg containers
	Part B	21.0 kg containers
	Part A+B	30.0 kg ready to mix units
Shelf life	12 months from date of production	
Storage conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.	
Appearance and colour	Pebble grey	
	Resin - part A:	light brown, liquid
	Hardener - part B:	transparent, liquid

SUSTAINABILITY

LEED Rating:

Sikafloor®-350 N Elastic conforms to the requirements of LEED EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings
SCAQMD Method 304-91 VOC Content < 100 g/l

APPROVALS / CERTIFICATES

- Coating for concrete protection according to the requirements of EN 1504-2:2004 and the EN 13813:2002, DoP 0208010402500000011008 certified by Factory Production Control Body, 0921 and provided with the CE-mark.
- Certified as part of the Surface Protection System OS 11a according to DIN EN 1504-2 and DIN V 18026.
- Certified as part of the Surface Protection System OS 11b according to DIN EN 1504-2 and DIN V 18026.
- Reaction to Fire classification according to DIN EN 13501-1. Test institute Hoch Report No. KB-Hoch-101213 and MPA Dresden Report No. 2007-B-0181/8

Density	Part A:	~ 1.83 kg/l
	Part B:	~ 1.02 kg/l
	Part A+B:	~ 1.18 kg/l

Density value at +23°C.

Solid content by mass ~100%

Solid content by volume ~100%

TECHNICAL INFORMATION

Shore A hardness ~60 (14 days / +23°C) (DIN 53505)

Tensile strength ~ 5.0 N/mm² (14 days / +23°C) (DIN 53504)

Tensile strain at break ~ 500% (14 days / +23°C) (DIN 53504)

SYSTEM INFORMATION

Systems

Please refer to the System Data Sheet of:

Sikafloor® MultiFlex PB-51 UV

Broadcast unicolour high performance polyurethane floor covering over elastic membrane with UV sealer

Sikafloor® MultiFlex PB-52

Broadcast unicolour high performance polyurethane floor covering with top sealer over elastic membrane

Sikafloor® MultiFlex PB-52 UV

Broadcast unicolour high performance polyurethane floor covering with top sealer over elastic membrane with UV sealer

APPLICATION INFORMATION

Mixing ratio Part A : part B = 30 : 70 (by weight)

Consumption ~ 1.2 kg/m²/mm. Please refer to the respective System Data Sheet

Ambient air temperature +10°C min. / +30°C max.

Relative air humidity 80% r.h. max.

Dew point

Beware of condensation!

The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

Substrate temperature +10°C min. / +30°C max.

Substrate moisture content

< 4% pbw moisture content.

Test method: Sika®-Tramex meter, CM - measurement or Oven-dry-method. No rising moisture according to ASTM (Polyethylene-sheet).

Pot Life

Temperatures

+10°C

+20°C

+30°C

Time

~ 60 minutes

~ 30 minutes

~ 15 minutes

Curing time

Before overcoating Sikafloor®-350 N Elastic broadcast allow:

Substrate temperature	Minimum	Maximum
-----------------------	---------	---------

+10°C

24 hours

*

+20°C

15 hours

*

+30°C

8 hours

*

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

* No max. waiting time if fully broadcast surface is free from all contaminations.

Applied product ready for use	Temperature	Foot traffic	Light traffic	Full cure
	+10°C	~ 24 hours	~ 5 days	~ 10 days
	+20°C	~ 15 hours	~ 3 days	~ 7 days
	+30°C	~ 8 hours	~ 2 days	~ 5 days

Note: Times are approximate and will be affected by changing ambient conditions

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Substrate quality & Preparation

Please refer to Sika Method Statement: "EVALUATION AND PREPARATION OF SURFACES FOR FLOORING SYSTEMS".

Application instructions

Please refer to Sika Method Statement: "MIXING & APPLICATION OF FLOORING SYSTEMS".

Maintenance

Please refer to "Sikafloor®- CLEANING REGIME".

IMPORTANT CONSIDERATIONS

Do not apply Sikafloor®-350 N Elastic on substrates with rising moisture. Freshly applied Sikafloor®-350 N Elastic must be protected from damp, condensation and water for at least 24 hours.

Uncured material reacts in contact with water (foaming). During application care must be taken that no sweat drops into fresh Sikafloor®-350 N Elastic (wear head and wrist bands).

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking. If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material

must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

MIXING

Prior to mixing, stir part B mechanically. When all of part A has been added to part B, mix continuously for 2 minutes until a uniform mix has been achieved.

When parts A and B have been mixed, add the quartz sand 0.1 - 0.3 mm and mix for a further 2 minutes until a uniform mix has been achieved. To ensure thorough mixing pour materials into another container and mix again to achieve a consistent mix. Over mixing must be avoided to minimise air entrainment.

Mixing Tools:

Sikafloor®-350 N Elastic must be thoroughly mixed using a low speed electric stirrer (300 - 400 rpm) or other suitable equipment.

APPLICATION

Sikafloor®-350 N Elastic is poured and spread evenly by means of a serrated/notched trowel. Then, level and remove entrained air with a spiked roller.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use.

Hardened and/or cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a

particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

Product Data Sheet

Sikafloor®-350 N Elastic

April 2023, Version 02.02

020812040020000013

