

PRODUCT DATA SHEET

LANKO® 753 Acrylic Additive

ACRYLIC ADDITIVE FOR MORTARS

DESCRIPTION

LANKO® 753 Acrylic Additive is a flexible additive designed for use with Sika and Lanko mortar systems. LANKO® 753 Acrylic Additive will improve the strength, increase the adhesion, water resistance and flexibility of any mortar system to which it is added.

USES

- LANKO® 753 Acrylic Additive may be used as an additive with Sika and Lanko cement-based technical mortars, in particular mortars for floor levelling, screeding, rendering, patching and repair.
- LANKO® 753 Acrylic Additive can be used in conjunction with neat cement as a bonding coat prior to the application of any mortar system.
- LANKO® 753 Acrylic Additive can also be used as an additive for any of Sika and Davco's range of ceramic tile adhesives and grouts.
- LANKO® 753 Acrylic Additive will not affect the flow characteristics of mortar products and is UV stable.

PRODUCT INFORMATION

Packaging	5 L containers
Shelf life	12 months
Storage conditions	Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 5 °C and 35 °C.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Do not allow the product to freeze.

FEATURES

- Flexible acrylic additive for screeds and renders
- Increases flexibility, strength and water resistance of cementitious products
- Used to increase mortar adhesion

- Do not use the product in temperatures below 5 °C or above 35 °C.
- Not to be used over non-porous surfaces, such as power trowelled or steel floated concrete. Refer to surface preparation section for instructions.
- Do not use on highly porous slabs, or in hot windy conditions without prior wetting down the slab – see application instructions for the individual mortar product for specific application information

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

- Surfaces, must be dry, structurally sound, clean, free of dust, dirt, wax, oil, grease, asphalt, mastic, latex compounds, adhesives, paint, gypsum based products, and other contaminants.
- All concrete sub-floors must be fully cured and dry, in accordance with AS 1884:2021 (maximum relative humidity of 80 %). They must be free of laitance, loose or deteriorated concrete, curing or form release agents, other contaminants and have a wood float finish. For sub-floors with a high moisture content or subject to rising damp, apply Sikalastic® Moisture Seal. Refer to datasheet for specific instructions.
- Non-porous surfaces, such as power trowelled or steel floated concrete, must be primed with Sikalastic® Moisture Seal. Alternatively, they can be acid etched or mechanically abraded.
- Deeply contaminated substrates must be abraded to a clean, sound surface or some substrates can be prepared with the use of Sikalastic® Moisture Seal – a bonding coat for contaminated surfaces. Contact the Sika Technical Service for further details on the suitability of Sikalastic® Moisture Seal over different contaminants.
- Rendered surfaces must be allowed to cure for at least 7 days.
- Old concrete and rendered surfaces must be thoroughly cleaned prior to using LANKO® 753 Acrylic Additive.
- Ensure release agents are removed from cement surfaces, especially tilt-up slabs.

MIXING

LANKO® 753 Acrylic Additive needs to be diluted prior to use. Under most circumstances, it is recommended to dilute LANKO® 753 Acrylic Additive 1 part with 2 parts water. This is then mixed and gauged, according to the specific mortar being used – refer to individual products for exact mix details.

APPLICATION METHOD / TOOLS

Refer to individual mortar datasheets for details on application techniques and tools.

Sika Australia Pty Limited
ABN 12 001 342 329
aus.sika.com
Tel: 1300 22 33 48

CLEANING OF EQUIPMENT

Excess LANKO® 753 Acrylic Additive and tools can be cleaned with water prior to drying.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

LANKO753AcrylicAdditive-en-AU-(05-2026)-1-1.pdf

Product Data Sheet
LANKO® 753 Acrylic Additive
May 2026, Version 01.01
020301010010000290