


## REFURBISHMENT CONCRETE REPAIR SITE HANDBOOK

HAND PLACED AND SPRAYED APPLICATIONS



**BUILDING TRUST** 

### CONCRETE REPAIR SITE HANDBOOK



 Sika MonoTop<sup>®</sup>/ SikaTop<sup>®</sup> Armatec<sup>®</sup>

> Reinforcement corrosion protection and bonding primers

Sika MonoTop<sup>®</sup>, SikaTop<sup>®</sup>
 Repair and profiling mortars

3. Sika MonoTop<sup>®</sup>, SikaTop<sup>®</sup>

Pore sealer/smoothing mortars

4. Sikagard®

Protective coatings and hydrophobic impregnations

### CONTENT

BEFORE	APPL	ICATION

- 4 Health and Safety
- 5 Technical and Safety Information
- 6 Bag Layout
- 7 Climate Conditions
- 8 Equipment

#### CONCRETE REPAIR PROCEDURE

- 10 1 Substrate Preparation
- 12 2 Reinforcement Preparation
- 13 3 Reinforcement Corrosion Protection
- 14 4 Bonding Primer
- 15 5a Repair Application by Hand
- 16 5b Repair Application by Spray
- 17 6 Smoothing Mortar

#### AFTER APPLICATION

18 Curing Protection / Curing Methods

#### ADDITIONAL INFORMATION

- 19 Mixing One-, Two-, and Three-Component Products
- 20 Overhead Application
- 21 Cleaning Tools / Environment / Accidents

#### SIKA REPAIR SYSTEMS

22 Concrete Overview

#### WE ARE SIKA

24 Sika is on Your Project Site

### HEALTH AND SAFETY

# TECHNICAL AND SAFETY INFORMATION





#### METHOD STATEMENT

- Repairing Concrete
  Using Sika<sup>®</sup> Ready
  to use Mortars
- Detailed stepby-step guide to concrete repair



### PRODUCT DATA SHEET

- Product uses
- Substrate quality
- Substrate
  preparation
- Mixing ratio
- Application conditions and tools
- Pot life
- Curing treatment
- Limitations



#### SAFETY DATA SHEET

- Hazards
- First aid
- Emergency
- Ecology

CONSULT PRODUCT DATA SHEET AND SAFETY DATA SHEET BEFORE STARTING WORK.

### BAG LAYOUT

### EXAMPLE



#### 1. PRODUCT NAME

#### 2. PRODUCT CHARACTERISTICS

3. BAG SIZE

#### 4. FEATURES AND INFORMATION

### CLIMATE CONDITIONS

#### STORAGE


- Dry and cool conditions
- Undamaged original packaging



#### APPLICATION

Protect area from:

- Direct sunlight
- Wind
- Rain
- Frost



#### TEMPERATURE

Check acceptable limits:

- Ambient temperature
- Substrate temperature

DO NOT MIX AND APPLY THE PRODUCT IN DIRECT SUNLIGHT.




### EQUIPMENT

### HAND TOOLS






## SPRAY EQUIPMENT



#### DRY SPRAY PROCESS



### **1 SUBSTRATE PREPARATION**

#### SURFACE PREPARATION

Mark defective concrete



#### CONCRETE REMOVAL

 Using a high pressure water jet, 1,100 bar (large area)



#### or

■ With a hammer drill (medium area)



#### or

Hammer and chisel (small patch repairs)

REMOVE TIE WIRES, NAILS ETC. REMOVE ONLY DEFECTIVE CONCRETE AS INSTRUCTED.

DO NOT REDUCE STRUCTURAL INTEGRITY.



#### EXTENT OF CONCRETE REMOVAL

 Remove concrete minimum 15 mm behind main bars



#### CORRECT SUBSTRATE PREPARATION

- Rough surface (2 mm minimum)
- Cut sides more than 90° to avoid undercutting and maximum 135° to reduce debonding around edges
- Substrate shall be sound with no loose material



#### INFORM A SUPERVISOR IMMEDIATELY IF THERE ARE ANY CRACKS IN THE SUBSTRATE.

### 2 REINFORCEMENT PREPARATION

### **3 REINFORCEMENT** CORROSION PROTECTION

#### CLEANING REINFORCEMENT

- Remove ALL: Tie wires
- Mortar/concrete
- Rust/scale Other loose material



#### **REMOVAL TECHNIOUES**

- 1. Steel wire brush or hand/power tools Technique applicable only in carbonated concrete and under environmental constraints where techniques 2 and 3 cannot be used.
- Reinforcement uniformly cleaned

#### 2. Abrasive blast cleaning techniques

- Reinforcement uniformly cleaned
- If chlorides are present reinforcement should be cleaned with water afterwards

#### 3. High pressure water jetting (1100 bar min)

Reinforcement uniformly cleaned







#### APPI ICATION OF CORROSION PROTECTION

Apply two 1 mm thick coats (total 2 mm minimum)



#### APPLICATION TECHNIQUES

Hopper spray for large applications



#### or

- Brush for small applications
- Inspect bars after to ensure full coverage



### 4 BONDING PRIMER

#### APPLYING BONDING PRIMER

(if specified)■ Wet the substrate



#### Wipe away excess water



with sponge

Large area

Large area: with air pressure

#### APPLICATION TECHNIQUES

■ For small patches brush firmly onto surface



■ For large areas spray on with hopper gun POINT GUN AT DIFFERENT ANGLES ON THE SURFACE TO ENSURE EVEN APPLICATION BEHIND THE BARS.

### 5a REPAIR APPLICATION BY HAND

#### SURFACE PREPARATION

(if no bonding primer applied)Wet the substrate



#### Wipe away excess water



Large area: with air pressure



#### APPLICATION TECHNIQUES

 Press the repair mortar firmly into the repair area using a trowel and/or hand
 APPLY SECOND COAT, WHEN FIRST COAT IS
 DRY (IF APPLICATION DEPTH EXCEEDS
 PRODUCT'S MAXIMUM COAT THICKNESS).

Profile the surface and finish with a trowel
 FOR BEST RESULTS, FINISH THE SURFACE
 WITH A PVC OR WOODEN TROWEL.

DO NOT SPRAY ADDITIONAL WATER OVER THE SURFACE.





### 5b REPAIR APPLICATION **BY SPRAY**

#### SURFACE PREPARATION

 Wet the substrate (if no bonding primer applied)



#### Wipe away excess water



with sponge

Small area:

Large area: with air pressure

#### APPLICATION TECHNIOUE

Point nozzle 200 mm to 500 mm from surface



Einish with a PVC or wooden trowel



### 6 SMOOTHING MORTAR

#### SURFACE PREPARATION

Wet and clean the surface with water (180 bar)



#### SMOOTHING OR LEVELLING MORTAR

- Apply vertically using toothed trowel
- Apply with trowel approximate 45° to surface

■ When the first coat is hard, apply second coat





After product has set, smooth surface using a wooden trowel







### AFTER APPLICATION

Rain\*

Sun\*



### cracking / crazing

Erost

Wind\*

CURING PROTECTION

Protect application from:

#### CURING METHODS

- Plastic sheeting
- Fabric and water
- Other membranes



If no subsequent coating is to be applied on the surface an approved curing agent (e.g. Sika<sup>®</sup> Antisol<sup>®</sup>) could be used.



### ADDITIONAL INFORMATION

Mixing

#### **ONE-COMPONENT SYSTEM**

(e.g. Sika MonoTon®)

 Add powder to water and mix at least for 3 minutes with a low speed mixer

#### TWO-COMPONENT SYSTEM (e.g. SikaTop®)

- Shake component A thoroughly and pour into a clean container
- Add in powder component B and mix at least for 3 minutes




#### THREE-COMPONENT SYSTEM


(e.g. SikaTop® Armatec EpoCem®)


- Shake component A + B separately
- Mix components A + B together

Add A + B to powder component C and mix for at least 3 minutes with a low speed mixer









## ADDITIONAL INFORMATION

### Overhead application

 Apply mortar tightly behind reinforcement until bars are covered



 Press firmly to ensure pores in concrete substrate are filled



- From same end apply second coat in same direction as first
- Repeat coats until void is filled



Smooth surface using a wooden trowel

## Cleaning tools / environment / accidents

#### **CLEANING TOOLS**

• Clean immediately with water after use.

HINTS AND ADVICE

Hardened material can only be removed mechanically.



#### ENVIRONMENT

- Dispose of waste responsibly
- Separate recycling materials



#### ACCIDENTS

 Seek immediate medical attention in the event of an injury



### SIKA CONCRETE REPAIR SYSTEMS

PRODUCT	ТҮРЕ	APPLICATI	ON METHODS	DESCRIPTION
Sika MonoTop®-352 NFG	Light Weight Structural Repair Mortar	Hand	Wet sprayed	R3 Normal setting, 4-75mm
Sika MonoTop®-412 NFG	Structural Repair Mortar	Hand	Wet sprayed	R4 Normal setting, 6-50mm
Sika MonoTop®-612N	Structural Repair Mortar	Hand	Wet sprayed	R4 Normal setting, 5-100mm
Sika MonoTop®-436N	Structural Repair Mortar	Form Pour		R4 Normal setting, 30-300mm
SikaQuick®-2500 (au)	Rapid Hardening Mortar	Hand		Very rapid hardening, gain early strength, 5-150mm
SikaGunite®-GP	Structural Repair Mortar	Dry Spray		General purpose gunite dry spray, 20-150mm
Sika MonoTop®-FC	Fairing Coat	Hand	Wet sprayed	Up to 3mm
Sika MonoTop®-723N	Smoothing Mortar	Hand	Wet sprayed	R3 mortar, 1-5mm
SikaGard®-720 Epocem®	Damp Substrate Pore Sealer	Hand	Wet sprayed	R4 Epoxy cement
Sika MonoTop®-910N	Bonding primer and reinforcement corrosion protection	Hand	Wet sprayed	Normal use
SikaTop®-110 Epocem®	Bonding primer and reinforcement corrosion protection	Hand	Wet sprayed	Demanding use
Sikadur® 32	Bonding primer	Hand	Wet sprayed	Long open life

# EVERYDAY, EVERYWHERE SIKA IS ON YOUR PROJECT SITE

**YOU CAN RELY ON** our experienced construction experts available in every phase of the construction process for valuable advice: from the initial consultation phase, through the project planning phase, the detailed design phase, application on site and finishing with quality control, completion and final handover.

Our knowhow in projects is based on more than 100 years of onsite experiences, which enables us to provide recommendations and long-lasting solutions for any project you have, no matter how large or small. Such projects include:

#### CIVIL ARCHITECTURE

- Residential buildings
- Educational buildings
- Office buildings
- Transportation buildings
- Cultural buildings
- Sports facilities
- Commercial buildings
- Healthcare facilities
- Communication facilities
- Judiciary buildings
- Landscape architecture
- Mixed-use highrise buildings
- Other domestic buildings /
- structures

#### INDUSTRIAL FACILITIES

- Research / lab / test buildings
- Industrial buildings
- Other industrial structures

#### INFRASTRUCTURE

- Water infrastructure
- Transportation infrastructure
- Power plants
- Mining
- Other infrastructure





### GLOBAL BUT LOCAL PARTNERSHIPS



#### WE ARE SIKA

Sika is a specialty chemicals company with a leading position in the development and production of systems and products for bonding, sealing, damping, reinforcing and protecting in the building sector and the motor vehicle industry. Sika's product lines feature concrete admixtures, mortars, sealants and adhesives, structural strengthening systems, flooring as well as roofing and waterproofing systems.



sika.com.au **1300 22 33 48** 

**BUILDING TRUST**