

PRODUCT DATA SHEET

SikaForce®-840 L07

Structural elastic 2-component polyurethane adhesive

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	SikaForce®-840 L07 (A)	SikaForce®-840 (B)
Chemical base	Polyol	Isocyanate
Colour (CQP001-1)	Black	Black
Density (uncured)	1.16 g/cm ³	1.27 g/cm ³
	mixed (calculated)	1.21 g/cm ³
Mixing ratio	by volume by weight	100 : 100 100 : 109.5
Viscosity (CQP029-4)	at 10 s ⁻¹	22 Pa·s ^A 60 Pa·s ^A
Application temperature	15 – 30 °C	
Open time (CQP046-11 / ISO 4587)	7 minutes ^{B, C}	
Handling time (CQP046-11 / ISO 4587)	20 minutes ^{B, C}	
Shore A hardness (CQP023-1 / ISO 48-4)	95 ^B	
Tensile strength (CQP036-2 / ISO 527)	15 MPa ^{B, D}	
Elongation at break (CQP036-2 / ISO 527)	100 % ^{B, D}	
E-Modulus (CQP036-2 / ISO 527)	elongation 0.05 – 0.25 %	350 MPa ^{B, D}
Tensile lap-shear strength (CQP046-9 / ISO 4587)	15 MPa ^{B, C, D}	
Glass transition temperature (CQP509-1 / ISO 6721-2)	-45 °C ^D	
Shelf life	12 months ^E	

CQP = Corporate Quality Procedure

A) tested at 20 °C

B) 23 °C / 50 % r. h.

C) adhesive layer: 25 x 12.5 x 1.5 mm

D) cured for 1 week at 23 °C

E) storage between 10 and 30 °C

DESCRIPTION

SikaForce®-840 L07 is a flexible, structural 2-component polyurethane adhesive, which cures at room temperature.

It is designed for bonding composite or coated metal components with stable properties over large temperature span. The adhesive is characterized by fast curing and strength build-up. While uncured, it has very good non-sag and compressibility behavior.

PRODUCT BENEFITS

- Combination of structural properties and flexibility
- Stable mechanical properties over wide temperature range
- Fast curing at room temperature and suitable for quick assembly
- Good non-sag behavior
- Excellent compressibility
- Low smell
- Does not contain solvents or PVC

AREAS OF APPLICATION

SikaForce®-840 L07 is suitable for structural elastic bonding of composites (e.g., CFRP, GFRP) or coated metals in transportation and general industry.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

CURE MECHANISM

SikaForce®-840 L07 cures by chemical reaction of the two components at room temperature. Higher temperatures accelerate the cure rate and decrease the open time. High humidity reduces the open time as well. In big bead applications, the generated exothermic heat of reaction can speed up the cure, reducing working and handling times.

After the open time is reached, the cure reaction proceeds very fast and the viscosity will increase significantly within minutes.

CHEMICAL RESISTANCE

In the view of potential chemical or thermal exposure, it is required to conduct a project related testing.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free from grease, oil and dust. Additional surface treatment depends on the specific nature of the substrates and is crucial for long lasting bond. All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

Application

Cartridge: Extrude adhesive without mixer to equalize the filling levels. Attach the mixer and dispose the first few cm of the bead prior to the application.

If SikaForce®-840 L07 is dispensed from dual cartridges, it is recommended to use a pneumatic or electric piston gun. SikaForce®-840 L07 can also be processed from pails with adequate 2-component equipment.

If dispensed with 2-component equipment, the mixer needs to be tailored for the specific application.

For advice on selecting and setting up a suitable pump system, contact the System Engineering Department of Sika Industry.

Removal

Uncured SikaForce®-840 L07 may be removed from tools and equipment with Sika® Remover-208 or another suitable solvent.

Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

STORAGE CONDITIONS

SikaForce®-840 L07 has to be kept between 10 °C and 30 °C in a dry place. Do not expose it to direct sunlight or frost. After opening of the packaging, the content has to be protected against humidity.

The lowest allowed temperature during transport is -20 °C for max. 7 days.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets

PACKAGING INFORMATION

SikaForce®-840 L07 (A+B)

Dual cartridge	400 ml
Mixer: Sulzer MixPac™ MFQ 08-24T	

SikaForce®-840 L07 (A)

Pail	23 l
------	------

SikaForce®-840 (B)

Pail	23 l
------	------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

SikaForce®-840 L07
Version 04.01 (06 - 2023), en_AU
012104588400001000

Sika Australia Pty Limited

ABN 12 001 342 329
aus.sika.com
Tel: 1300 22 33 48

