

## PRODUCT DATA SHEET

# Sikasil<sup>®</sup>-728 NS

Non-sag, ultra-low modulus, neutral cure silicone sealant for concrete pavements

### DESCRIPTION

Sikasil<sup>®</sup>-728 NS is a non-sag, one-component, ultra-low modulus, elastomeric, neutral cure silicone sealant designed to seal saw cut and expansion joints in concrete pavements.

### USES

Sikasil<sup>®</sup>-728 NS is designed to seal saw cut and expansion joints in concrete pavements on highways, airports, bridges, walkways, parking garages, and driveways. Suitable substrates for Sikasil<sup>®</sup>-728 NS are concrete, steel, glass, aluminium, masonry, brick and natural stone.

### CHARACTERISTICS / ADVANTAGES

- Very high movement capability
- Very good adhesion, especially to concrete
- Very long service life due to outstanding UV resistance
- Very good flexibility for use in extremely high and low temperatures
- Resistance to jet fuel and road salts
- Non-sag, can also be used in vertical joints

### APPROVALS / CERTIFICATES

- ASTM D 5893 Type NS
- ASTM C 920, Type S, Grade NS, Class 100/50, Use T<sub>2</sub>, NT, M, G, A, O
- TT-S-00230C, Type II, Class A
- US Federal Specification SS-S-200E Flame Resistance (section 4.4.12)
- FAA AC 150/5370-10G Item P-605
- NSW RMS QA Specification R83: Concrete Pavement Base (Ed. 3/Rev, 0, Nov.2013)
- QLD TMR Technical Specification MRTS77: Bridge Deck (Jun. 2011)

### PRODUCT INFORMATION

Composition	Neutral cure silicone
Packaging	600 ml sausage, 20 sausages per box
Shelf life	Sikasil <sup>®</sup> -728 NS has a shelf life of 12 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Sikasil <sup>®</sup> -728 NS shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Colour	Limestone, Charcoal Grey
Density	~1.30 kg/l (ISO 1183-1)

### TECHNICAL INFORMATION

Shore A hardness	~10 (after 21 days)	(ASTM C 661, ASTM D 2240, ISO 868)																		
Tensile strength	~1.20 MPa	(ASTM D 412)																		
Tensile stress at specified elongation	~0.24 MPa at 100 % elongation ~0.30 MPa at 150 % elongation	(ASTM D 412)																		
Tensile strain at break	~1 000 % ~900 %	(ASTM D 412) (ISO 37)																		
Movement capability	+100 % / -50 %	(ASTM C 719)																		
Adhesion in peel	~7 N/mm on mortar substrate	(ASTM C 794)																		
Service temperature	-60 °C min. / +175 °C max.																			
Chemical resistance	Sikasil®-728 NS is resistant to water, road salts, seawater, diluted alkalis, cement slurry and water dispersed detergent. Sikasil®-728 NS is temporarily resistant to jet fuel spillage. Sikasil®-728 NS is not resistant to alcohols, organic acids, concentrated alkalis and acids and chlorinated hydrocarbons.																			
Resistance to weathering	0 (no cracks)	(ASTM C 793)																		
Joint design	<p>The spacing between joints and joint dimensions must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be <math>\geq 6</math> mm and <math>\leq 25</math> mm. The joint depth shall be between 0.5 and 0.8 as a ratio of the joint width (width:depth ratio of 2:1 – 1:0.8) but always <math>\geq 6</math> mm and <math>\leq 13</math> mm. The joint shall be recessed half of the joint width but always <math>\geq 10</math> mm. For larger joints, please contact Sika technical service.</p> <p><b>Standard joint dimensions for joints between concrete elements</b></p> <table border="1"> <thead> <tr> <th>Joint width [mm]</th> <th>Joint depth [mm]</th> <th>Recessed below surface [mm]</th> </tr> </thead> <tbody> <tr> <td>6</td> <td>6</td> <td>10</td> </tr> <tr> <td>10</td> <td>6</td> <td>10</td> </tr> <tr> <td>15</td> <td>8</td> <td>10</td> </tr> <tr> <td>20</td> <td>10</td> <td>10</td> </tr> <tr> <td>25</td> <td>13</td> <td>13</td> </tr> </tbody> </table> <p>All joints must be correctly designed and dimensioned in accordance with the relevant standards before their construction. The basis for calculation of the necessary joint widths are the type of structure and its dimensions, the properties of the adjacent building materials and the joint sealing material, as well as the specific exposure of the building and the joints.</p>		Joint width [mm]	Joint depth [mm]	Recessed below surface [mm]	6	6	10	10	6	10	15	8	10	20	10	10	25	13	13
Joint width [mm]	Joint depth [mm]	Recessed below surface [mm]																		
6	6	10																		
10	6	10																		
15	8	10																		
20	10	10																		
25	13	13																		

## APPLICATION INFORMATION

Sag flow	0 mm 0 mm non-sag	(ASTM D 2202) (ASTM C 639)
Ambient air temperature	+5 °C min. / +40 °C max. min. 3 °C above dew point temperature	
Substrate temperature	+5 °C min. / +40 °C max. Sealants should be installed when substrates are at mid-range of their anticipated movement.	
Backing material	Use closed cell, polyethylene foam backing rods 25 % larger than the joint width. If the joint depth does not allow for a backer rod, use polyethylene bond breaker tape to prevent three-sided adhesion.	
Curing rate	~3.5 mm/d (23 °C / 50% r.h.)	(CQP 049-2)
Skinning time	~20 min (23 °C / 50 % r.h.)	(ISO 019-1, MNA Method)

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Safety Data Sheet
- Pre-treatment Chart Sealing and Bonding

## IMPORTANT CONSIDERATIONS

- Do not allow Sikasil®-728 NS to come in contact with solvents during curing.
- Do not allow Sikasil®-728 NS to come in contact with uncured polyurethane sealants during curing.
- Do not use Sikasil®-728 NS to seal joints in and around swimming pools.
- Do not use Sikasil®-728 NS for joints under water pressure or for permanent water immersion.
- Do not use Sikasil®-728 NS for structural sealing.
- Do not use Sikasil®-728 NS on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Before using Sikasil®-728 NS on natural stone, contact Sika technical service for advice.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sikasil®-728 NS adheres without primers and/or activators.

However, for optimum adhesion and critical, high performance applications, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed:

#### Porous substrates

Concrete shall be primed with Sika® Primer-3 N applied with a clean brush. Before sealing allow a flash-off time of > 30 minutes (< 8 hours).

#### Non porous substrates

On aluminium, anodised aluminium, stainless steel and galvanised steel, Sika® Aktivator-205 shall be applied using a clean towel. Before sealing allow a flash-off time of > 15 minutes (< 8 hours).

For detailed advice, please contact Sika technical ser-

vice.

### APPLICATION METHOD / TOOLS

Sikasil®-728 NS is supplied ready to use.

After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Sikasil®-728 NS can be applied into the joint using a sealant gun for cartridges and sausages, or a pump or other bulk dispensing equipment for bulk packaging. The joint should be filled from the bottom taking care to avoid any air entrapment and ensure full contact with the joint sides. The sealant must be firmly tooled against the joint sides to ensure adequate contact and adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.