



MVER
TOLERABLE



SMOOTH
QUALITY

Sika® Level SkimCoat

FAST SETTING, SMOOTHING AND FINISHING COMPOUND

- Levels new and old floors
- Re-workable up to 30 minutes after mixing; No additional water needed
- No MVER (Moisture Vapor Emission Rate) limits
- For Interior use only

SIKA.COM.AU
1300 22 33 48



SikaAustralia



sika_australia



Sika Australia

BUILDING TRUST



Sika® Level SkimCoat

FAST SETTING, SMOOTHING AND FINISHING COMPOUND

WHERE TO USE

- For Interior use only
- Concrete, wood subfloors, ceramic and quarry tiles
- Minor defects, holes, and cracks in concrete and wood subfloors
- Pre-fill non-moving joints and seams
- Radiant heating systems

FEATURES AND BENEFITS

















- Easy to prepare and quick to apply
- True feather edge material
- Zero VOC's
- Levels new and old floors
- Adhesion to substrates, subfloors and stable adhesive residue.
- Rapid setting
- Excellent standard of finish can be achieved to allow direct application of floor coverings

NOTE: Always refer to current PDS and SDS for detailed performance specifications prior to use.

TYPICAL DATA (Material and curing conditions @ 23°C and 50% R.H.)

Color	Grey
Application Thickness	Feather edge - 13 mm
Working Time	10 to 20 mins
Set Times	Initial: 20 to 30 mins Final: 30 to 60 mins
Compressive Strength (ASTM C109)	3,700 psi (25 MPa) at 28 days
Flexural Strength (ASTM C348)	1,300 psi (9 MPa) at 28 days
Flammability (ASTM E84)	Flame Spread 0; Smoke Development 0
VOC (EPA METHOD 24)	0 g/l

Sika® Level SkimCoat

Strength					
Smoothness					
Depth					
Speed					



Sika Australia Pty Ltd

55 Elizabeth Street, Wetherill Park NSW 2164

Phone: 1300 22 33 48 • sika.com.au

BUILDING TRUST

