



BUILDING TRUST



PRODUCT DATA SHEET

Davco® Superfine White Grout

A BRIGHT WHITE SMOOTH FINISH CEMENT BASED GROUT

DESCRIPTION

Davco® Superfine White Grout is an bright white, unsanded, Sanitized®, smooth finish cement based grout resistant to a broad spectrum of moulds and bacteria. Davco® Superfine White Grout is suitable for wall applications internally for joints from 1 - 3mm.

USES

Davco® Superfine White Grout is suitable for most types of tiles and natural stone.
Davco® Superfine White Grout is suitable for both commercial and domestic wall applications including shower, bathroom and laundry walls where a bright white wall grout is required.

CHARACTERISTICS / ADVANTAGES

- Bright white appearance
- Suitable for wall applications only
- Sanitized®
- Mould & bacteria resistant
- Smooth finish
- For joints 1 - 3mm

PRODUCT INFORMATION

Packaging	1.5kg, & 5kg Plastic film bags 10kg, & 20kg Paper bags
Shelf life	Plastic film bags: if unopened grout shall remain usable for up to 18 months from date of manufacture. Paper bags: if unopened grout shall remain usable for up to 12 months from date of manufacture.
Storage conditions	Store grout in an elevated location, in dry cool conditions out of direct sunlight.
Product Declaration	AS ISO 13007.3 CG1
Bulk Density	1.3kg/L
Volatile organic compound (VOC) content	Low VOC - 3g/L (SCAQMD method 304-91)

APPLICATION INFORMATION

Mixing Ratio	5.5 - 6 Litres per 20kg bag		
Consumption	Quantity of grout required kg/m ²		
	Tile Size	1.5mm Joint	3mm Joint
	10x50x6mm	0.8kg	1.6kg
	150x150x6mm	0.3kg	0.6kg
	200x100x6mm	0.3kg	0.6kg
	200x200x6mm	0.2kg	0.4kg
	300x600x9mm	0.13kg	0.25kg
The coverage of the grout will vary depending upon the texture, size and thickness of the tile and the width of the grout joint. Use the table as a general guide only.			
Pot Life	40 Minutes at 23°C and 50% RH.		
Curing Time	24 hours at 23°C & 50% RH.		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Test the product in an inconspicuous area first.
- Not suitable for use in harsh and demanding environments or other areas where there are hygiene regulations and chemical resistance requirements. A Sika® epoxy grout should be used for these applications.
- Cleaning or discolouration problems may occur when used with textured, porous or natural stone tiles
- Do not use on floors
- Do not use on submerged applications including pools, ponds, spas or water features
- Do not use in movement joints.
- Product may be weakened or damaged when exposed to neat or strong acids.
- Product may not be suitable for stone sensitive to moisture, test prior to installation for compatibility.
- For other uses not mentioned in these instruction please contact <https://aus.sika.com/>

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Tools required;

- Mixing buckets & clean water
- Drill with mixing paddle
- Grout float / rubber squeegee
- Sponge & dry cloth
- Personal protective equipment

SURFACE PREPARATION

- Before commencing grouting, ensure the tile adhesive has set firmly. This usually requires 24 hours with the majority of tile adhesives depend on application conditions.
- Remove any spacer lugs, rake-out any excess adhesive and any loose or foreign material from the grout joints.
- In general, ensure the grout joints are clean and dry.

MIXING

1. The mixing ratio is 20kg of powder to 5.5-6L of potable water.
2. Add the water to a bucket, then slowly add the Davco Sanitized® Superfine White Grout powder to the water. Stir the mix until a lump-free toothpaste consistency is achieved.
3. Allow the mix to stand for 5 minutes, re-stir, then use the grout.
 - Note: Where movement is expected, or for superior performance in general applications, use Davco 4 in 1 Grout Additive instead of water alone. Refer to the Davco 4 in 1 additive data sheet for additional information.

APPLICATION

1. Prior to grouting it is advisable to lightly dampen the grout joints, particularly with porous tiles or in hot conditions.
2. Using a rubber float or squeegee, work the grout into the joints in a diagonal motion. Make sure the grout is worked into the joint (it should not bridge the joint).
3. Using a diagonal motion remove excess grout from the surface of the tiles with a rubber float or squeegee.
4. Clean up the remainder of the grout with a lightly dampened sponge. Regularly rinse the sponge out to help with cleaning and don't make it too wet.
5. Leave the grout to cure for 24 hours before cleaning the haze off with a dry cloth.

CLEANING OF TOOLS

Tools and surrounding areas should be cleaned up with water while grout is still soft and wet

MAINTENANCE INSTRUCTIONS

CLEANING

Davco® Superfine White Grout shall require routine maintenance and cleaning with a neutral detergent and water.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48



Product Data Sheet

Davco® Superfine White Grout

December 2025, Version 01.01

02172010000000101

DavcoSuperfineWhiteGrout-en-AUDAVCO-(12-2025)-1-1.pdf