

## PRODUCT DATA SHEET

# SikaBond®-130 Design Floor

Fibre-reinforced floor covering adhesive

### DESCRIPTION

SikaBond®-130 Design Floor is a 1-component, solvent-free, fibre-reinforced dispersion adhesive.

### USES

SikaBond®-130 Design Floor is designed for full surface bonding of mentioned below floor coverings on absorbent substrates in interior areas:

Luxury vinyl tiles (LVT)	PVC floor coverings
Cushioned vinyl (CV) floor coverings	Carpets with PVC or fleece backing
Impact sound insulation underlays	Single or multilayer needle felting

### CHARACTERISTICS / ADVANTAGES

- Very easily spread
- Low consumption / high coverage
- Fibre-reinforced
- High initial adhesion power, high final bonding strength
- Resistant to plasticizers
- Suitable for wet bonding
- Suitable for use with underfloor heating
- Suitable for use with castor-chairs
- Suitable for shampooing

### SUSTAINABILITY

- EMICODE EC1<sup>PLUS</sup>

### PRODUCT INFORMATION

<b>Composition</b>	1-Component dispersion	
<b>Packaging</b>	3 kg, 7 kg plastic pail	
<b>Shelf life</b>	SikaBond®-130 Design Floor has a shelf life of 12 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.	
<b>Storage conditions</b>	SikaBond®-130 Design Floor shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.	
<b>Colour</b>	Light beige	
<b>Density</b>	~1.25 kg/l	(ISO 1183-1)
<b>Consistency</b>	Middle viscous, spreads very easily	

### TECHNICAL INFORMATION

<b>Service temperature</b>	+5 °C to +35 °C
----------------------------	-----------------

### APPLICATION INFORMATION

<b>Consumption</b>	~250 g/m <sup>2</sup>	Trowel V1	PVC floor coverings with even backing, CV floor coverings.
	~300 -350 g/m <sup>2</sup>	Trowel V2	PVC floor coverings with structured backing, carpets with PVC backing, insulation underlays, Luxury vinyl tiles (LVT), Textile floor coverings, Needle felting.
<b>Ambient air temperature</b>	+15 °C to +35 °C		
<b>Relative air humidity</b>	40 % to 65 %		
<b>Substrate temperature</b>	During laying and until SikaBond®-130 Design Floor has fully cured, the substrate and ambient temperatures shall be between +15 °C and +35 °C without and between +20 °C and +35 °C with underfloor heating.		
<b>Substrate moisture content</b>	<p>Permissible substrate moisture content without underfloor heating:</p> <ul style="list-style-type: none"> <li>▪ 2.0 % CM for cement screeds. (ca. ~3.2% Tramax / Gravimetric weight percent)</li> <li>▪ 0.5 % CM for anhydrite screeds.</li> <li>▪ 3–12 % CM for magnesia flooring (depending on the organic content).</li> </ul> <p>Permissible substrate moisture content for use with underfloor heating:</p> <ul style="list-style-type: none"> <li>▪ 1.8 % CM for cement screeds. (ca. ~2.9% Tramax / Gravimetric weight percent)</li> <li>▪ 0.3 % CM for anhydrite screeds.</li> <li>▪ 3–12 % CM for magnesia flooring (depending on the organic content).</li> </ul> <p>Note: For all moisture contents and the quality of the substrates and surfaces always follow the guidelines of the soft floor manufacturer.</p>		
<b>Curing time</b>	~24 h (final strength after ~72 h)		
<b>Skin time / laying Time</b>	~20–30 min (depending on laying method)		
<b>Flash-off time</b>	~5–20 min		

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ive can no longer be used.

- Avoid extreme variations of environmental conditions (temperature or humidity).
- SikaBond®-130 Design Floor is only suitable for interior areas.

## FURTHER INFORMATION

- Safety Data Sheet

## IMPORTANT CONSIDERATIONS

- SikaBond®-130 Design Floor is only suitable for use by professional floor covering applicators.
- For good workability, the adhesive temperature shall be ≥ +15 °C.
- Thermal welding of seams should not be done earlier than 24 hours after installation (48 hours recommended).
- Floor coverings need to acclimatise to the room before installation according to the guidelines of the supplier.
- Protect from freezing. After being frozen the adhesive can no longer be used.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

For the application of SikaBond®-130 Design Floor all standard construction guidelines and relevant valid data sheets apply.

### SUBSTRATE PREPARATION

- The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed.
- SikaBond®-130 Design Floor adheres without primers and/or activators.
- The subfloor must meet the requirements of national standards, must have good compression and tensile strength and has to be even.
- Defective subfloors shall be treated by taking appropriate measures e.g. grinding, milling, vacuuming or priming.
- To produce an absorbent, even subfloor, a cement-based leveling compound shall be used. For appropriate layer thicknesses refer to the relevant valid data sheets.
- Mastic asphalt and other non-absorbent subfloors may require specific self-leveling compound layer thicknesses. For appropriate layer thicknesses refer to the relevant valid data sheets.
- Concrete and/or cement screeds must be ground and thoroughly cleaned with an industrial vacuum.
- When installing floor covering with underfloor heating, existing measuring points have to be checked regarding the moisture content of the subfloor.

### APPLICATION METHOD / TOOLS

Stir SikaBond®-130 Design Floor well before use. The adhesive has to be applied on the subfloor with a trowel. The type of trowel depends on the subfloor and the backing of the floor covering (refer to Consumption). Always assure sufficient transfer of the adhesive to the floor covering backing.

For wet phase bonding the floor coverings have to be laid in the relatively moist adhesive. All types of floor coverings need to be rubbed down well with an articulated floor roller, especially along the seams. After a waiting time of ~15 minutes the floor covering has to be rubbed down again. Avoid direct sunlight, direct high temperatures, dynamic stress and pointed stress.

The guidelines of the floor covering manufacturer apply.

Sika Australia Pty Limited

PO Box 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

### CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with water. Once cured, residual material can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaBond-130DesignFloor-en-AU-(04-2023)-3-2.pdf