

## PRODUCT DATA SHEET

# SikaShield® P44 MG Fidia 4,5 kg/m<sup>2</sup>

Plastomeric bituminous membrane surfaced with mineral granules and flexible at -10 °C  
(Formerly **Index Fidia Mineral**)

### DESCRIPTION

SikaShield® P44 MG Fidia 4,5 kg/m<sup>2</sup> is an APP modified bituminous roof waterproofing membrane with a weight of 4,5 kg/m<sup>2</sup>. It is reinforced with a non-woven polyester fabric dimensionally stabilised with glass fibre and is flexible at -10 °C. The top surface is coated with mineral granules, which allows the permanent exposure to UV radiation. The underside of the product has a burn-off film for easy torch-application.

### USES

The Product is used as a waterproofing membrane for:

- Balconies and terraces
- Flat or sloping roofs with up to 15 % gradient

The Product is used as a:

- Exposed cap sheet in a multi-layer system

### CHARACTERISTICS / ADVANTAGES

- Decorative mineral granules
- Easy to install by torching method
- Fully bonded
- Flexible in cold temperatures
- Good mechanical properties (tensile, tear, shear)
- Can be painted immediately after application
- Tiles can be placed directly onto the membrane

### APPROVALS / CERTIFICATES

- CE marking and declaration of performance based on EN 13707:2004+A2:2009 Flexible sheets for waterproofing — Reinforced bitumen sheets for roof waterproofing
- AS4654.1- 2012- Approved for external above ground use (Test certificate available upon request)

### PRODUCT INFORMATION

<b>Composition</b>	Composition Reinforcing material	APP modified bitumen non-woven polyester fabric dimensionally stabilised with glass fibre
<b>Packaging</b>	Roll width Roll length	1.0 m 10.0 m (EN 1848-1)
	Refer to current price list for packaging variations.	
<b>Shelf life</b>	36 months from date of production	
<b>Storage conditions</b>	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	

Appearance and colour	Top surface	Mineral Granules
	Bottom surface	Polyethylene film
	Top layer colour	Refer to current price list for color variations
Mass per area	Mass per unit area	4.5 kg/m <sup>2</sup> ± 0.45 kg/m <sup>2</sup> (EN 1849-1)

## TECHNICAL INFORMATION

Maximum tensile force	Longitudinal (MD)	450 N/50 mm ± 90 N/50 mm	(EN 12311-1)
	Transversal (CMD)	400 N/50 mm ± 80 N/50 mm	
Elongation at maximum tensile force	Longitudinal (MD)	40 % ± 15 %	(EN 12311-1)
	Transversal (CMD)	40 % ± 15 %	
Resistance to tear	Longitudinal (MD)	150 N ± 45 N	(EN 12310-1)
	Transversal (CMD)	150 N ± 45 N	
Joint shear resistance	Longitudinal	350 N/50 mm ± 70 N/50 mm	(EN 12317-1)
	Transversal	300 N/50 mm ± 60 N/50 mm	
Flexibility at low temperature	≤ -10 °C		(EN 1109)
Watertightness	Method B: 24 hours at 60 kPa	Pass	(EN 1928)
Reaction to fire	Class E		(EN 13501-1)

## APPLICATION INFORMATION

Ambient air temperature	Minimum	+5 °C
	Maximum	+40 °C
Relative air humidity	Maximum	80 %
Substrate temperature	Minimum	+5 °C
	Maximum	+40 °C

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Guidelines and good practice for torch-applied membranes
- Method Statement - Roofing Build-up with Bituminous Membranes

## ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

# APPLICATION INSTRUCTIONS

## SUBSTRATE QUALITY

### SYSTEM DESIGN

Consider the following when designing the roof system:

- The supporting structure must be of sufficient structural strength to support all new and existing layers of the roof build-up.
- The complete roof system must be designed to withstand and be secured against wind uplift loadings.
- The wind uplift resistance of the adhered roofing assembly is limited by the adhesion strength of the Product to the substrate.

### SUBSTRATE CONDITION

- The substrate surface must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, laitance, oil, dust and loosely adhering particles.

### SUBSTRATE PREPARATION

#### PRIMING

- Apply Sika® Igoflex P primer at a rate of 6-8m<sup>2</sup> per litre. Note: Consumption rates will vary depending on substrate type and porosity.
- Allow the primer to dry before membrane installation

## APPLICATION

### IMPORTANT

- At low temperatures, take care unrolling to avoid damaging the membrane.
- Use suitable footwear to avoid puncturing the membrane.
- Do not apply to wet, damp or unclean surfaces.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at 260 °C) will be damaged making the membrane un-useable.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps. If this occurs, un-bonded areas must be lifted and re-torched.
- If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

### ALIGNMENT

Unroll, align and re-roll correctly before torching.

### OVERLAPS

Side: 100mm. End: 150 mm.

### FASTENING

Fidia Polyester when used as a roofing base sheet, can be mechanically fixed on the substrate by using the correct type of fasteners. Contact Sika Technical Services for additional information.

### TORCHING

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the backing film starts to melt, the membrane is ready to stick. Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen

## DETAILING

Use a sharp knife to cut in all details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc. Refer to the relevant method statement for further information on detailing.

## MAINTENANCE

Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc.

Remove any leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system.

To maintain the function of the roof waterproofing membrane during its lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Australia Pty Limited**

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

**Product Data Sheet**

SikaShield® P44 MG Fidia 4,5 kg/m<sup>2</sup>

April 2023, Version 02.02

020920011990001635

SikaShieldP44MGFidia45kgm-en-AU-(04-2023)-2-2.pdf

