

Sika® Primer-209 D

Pigmented Primer for paints and plastics

Technical Product Data

Chemical base	Pigmented, solvent-based adhesion promoter
Colour	Black
Density (CQP ¹ 006-3 / ISO 2811-1)	1.0 kg/l approx.
Flash point (CQP 007-1 / ISO 13736)	-4°C
Solid content	30% approx.
Application temperature	5 - 40°C
Application	Brush, felt, foam applicator
Coverage	50 - 150 ml per m ² approx. depending on substrate porosity
Flash-off time ²	above 15°C 10 min below 15°C 30 min maximum 24 hours
Storage	Store in sealed container in a cool dry place below 25°C
Shelf life	9 months

¹) CQP = Corporate Quality Procedure ²) In specific applications temperature and flash-off time may be different

Description

Sika® Primer-209 D is a black, moisture-curing low viscous primer specifically formulated for the treatment of painted surfaces or plastics prior to application of Sikaflex® PUR adhesives.

Sika® Primer-209 D is manufactured in accordance with ISO 9001 / 14001 quality assurance system and the responsible care program.

Areas of Application

Sika® Primer-209 D is used to improve adhesion on the following substrates:

Paints

Acrylics, alkyds / melamine, powder coatings, baking varnishes

Plastics

Polymethylmethacrylate (PMMA), polycarbonate (PC), polystyrene (PS), glass fibre reinforced polyester (PES-GRP), glass fibre reinforced epoxy resins (EP-GRP), ABS, PVC, etc.

Due to the individual chemical composition of the formulations and specific surface conditions, we recommend to do adhesion tests on the substrates. Always seek the manufacturer's advice before using the primer on thermoplastics that are prone to stress cracking, such as acrylics, polycarbonates or ABS etc.

This product is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed to

ensure adhesion and material compatibility.

Method of Application

Surfaces must be clean, dry and free from grease, oil and dust. Adhesion on substrates might be improved by adding and/or combining pre-treatment processes such as scuffing, cleaning and activating.

Shake Sika® Primer-209 D very thoroughly until mixing ball rattles freely. Continue shaking for another minute. The primer may be applied with a brush or felt.

Apply Sika® Primer-209 D evenly as a single thin coat.

Ideal application and surface temperature is between 15°C and 25°C.

Consumption and method of application depend on the specific nature of the substrates and manufacturing process. Tightly re-seal container immediately after each use.

Important Note

Sika® Primer-209 D is a moisture reactive system. In order to maintain product quality it is important to reseal the container with the inner plastic liner immediately after use. Once the surface pre-treatment operation is completed the cap has to be screwed on.

Dispose the product of approx. one month after opening if used frequently or after 2 months in case of infrequent use.

If gelling, separation or a significant increase in viscosity is noted, discard the primer immediately.

Never dilute or mix this product with any other substances.

Further Information

Working instructions issued for a defined application may further specify technical data contained in this Product Data Sheet. Copies of the following publications are available on request:

- Safety Data Sheet
- Sika Pre-treatment Chart

Packaging Information

Can	250 ml
-----	--------

Value Bases

All technical data stated in this Product Data Sheet are laboratory test based. Current measured values may vary do to factors beyond our influences.

Health and Safety Information

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Material Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Australia Pty Limited
ABN 12 001 342 329

aus.sika.com
Tel: 1300 22 33 48

