

PRODUCT DATA SHEET

Sikafloor®-29 PurCem®

High strength, water-based polyurethane hybrid coving and detailing mortar

DESCRIPTION

Sikafloor®-29 PurCem® is a multi-component, polyurethane hybrid mortar. It has high impact and mechanical resistance, good resistance against chemicals and wear.

USES

Sikafloor®-29 PurCem® is used as a coving mortar, detailing and vertical rendering with Sikafloor® PurCem® floor systems.

CHARACTERISTICS / ADVANTAGES

- Good wear resistance
- High mechanical and impact resistance
- High softening point
- Good chemical resistance
- Non tainting / odourless
- Fast curing
- VOC free
- Can be applied to substrates with high moisture content (7 days old or mature damp concrete or 10% moisture pbw)

SUSTAINABILITY

LEED Rating:

USGBC LEED® Rating. Confirms Section FQ (Indoor Environment Quality), Credit 4.2 Low Emitting Materials Paints and Coatings (VOC content ≤ 50 g/l).

APPROVALS / CERTIFICATES

- Synthetic resin screed material according to EN 13813:2002, Declaration of Performance 02 08 02 02 003 0 000001 1088, certified by notified factory production control certification body 0086, certificate of conformity of the factory production control 541325, and provided with the CE marking.
- Coating for surface protection of concrete according to EN 1504-2:2004, Declaration of Performance 02 08 02 02 003 0 000001 1088, certified by notified factory production control certification body 0086, certificate of conformity of the factory production control 541325, and provided with the CE marking.
- EN1186, EN 13130, and prCEN/TS 14234 standards, and the Decree on Consumer Goods, representing the conversion of directives 89/109/EEC, 90/128/EEC and 2002/72/EC for contact with food stuffs, according to test report by ISEGA, 32758 U11 and 32759 U11, both dated December 6th, 2011. (Tests performed on Sikafloor® -20/21/22/29 and 31 PurCem® in standard and LP versions).
- British Standards Specifications (BSS) acceptance for use in the UK. Campden and Chorleywood Food Research Association, Ref. S/REP/125424/1a and 2a, dated 8th February, 2012
- Fire classification report according to EN 13501-1 from Exova Warrington Fire for Sikafloor®-31 PurCem® No.31050, dated 24th of March, 2012
- Liquid water transmission rate test report from the Technology Centre, Ref. 15456 dated January 25th, 2012
- Impact resistance values tested at PRA, Ref. No. 75221-151, dated January 11th, 2012

PRODUCT INFORMATION

Composition	Water-based polyurethane cement hybrid	
Packaging	Part A	1.30 kg plastic bottle
	Part B	1.50 kg plastic bottle
	Pigment	0.4 kg plastic tub
	Part C	1.60 kg kg plastic bag
	Part D	17.3 kg plastic bag
	Part A+B+C+D	22.0 kg ready to mix unit
Shelf life	Part A	9 months from date of production.
	Part B	6 months from date of production.
	Part C	6 months from date of production.
	Part D	Not applicable - (inert silica sand)
Storage conditions	The package must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.	
Appearance and colour	Part A	opaque liquid
	Part B	brown liquid
	Pigment	colour
	Part C	natural grey powder
	Part D	natural sand colour
Density	Part A+B+C mixed: ~ 1.97 kg/l ± 0.03 (at +20 °C)	

TECHNICAL INFORMATION

Shore D Hardness	~80–85	(ASTM D 2240)
Compressive strength	~44 N/mm ² (28 days at +23 °C / 50 % r.h.)	(BS EN 13892-2)
Tensile strength in flexure	~8 N/mm ² (28 days at +23 °C / 50 % r.h.)	(BS EN 13892-2)
Tensile adhesion strength	concrete failure	(EN 1542)

SYSTEM INFORMATION

Systems	As a coving mortar and render mortar in Sikafloor® PurCem® applications.
---------	--

APPLICATION INFORMATION

Mixing ratio	Part A : P : B : C : D = 1 : 0.3 : 1.1 : 1.2 : 13.3 (packaging size = 1.3 : 0.4 : 1.5 : 1.6 : 17.3) by weight. Mix full units only.	
Consumption	~ 2.0 kg/m ² /mm	
Layer thickness	3–9 mm	
Ambient air temperature	+10 °C min. / +40 °C max.	
Relative air humidity	85 % max.	
Dew point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.	
Substrate temperature	+10 °C min. / +40 °C max.	
Substrate moisture content	Can be installed on substrates with higher moisture content. No ponding water. Check rising moisture. The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 N/mm ² .	

Pot Life	Temperatures	Time
	+10 °C	~ 35–40 minutes
	+20 °C	~ 22–25 minutes
	+30 °C	~ 15–18 minutes
	+35 °C	~ 12–15 minutes

Curing time	Before overcoating Sikafloor®-29 PurCem® allow:		
	Substrate temperature	Minimum	Maximum
	+10 °C	20 hours	72 hours
	+20 °C	10 hours	48 hours
	+30 °C	5 hours	24 hours
	+35 °C	5 hours	24 hours

Times are approximate and will be affected by changing ambient and substrate conditions, particularly temperature and relative humidity.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Please refer to:

- Sikafloor® PurCem® Method Statement
- Sika® Method Statement Mixing and Application of Flooring Systems
- Sika® Method Statement Surface Evaluation & Preparation
- Sikafloor® PurCem® System Data Sheets

IMPORTANT CONSIDERATIONS

- Do not apply to PCC (polymer modified cement mortars) that may expand due to moisture when sealed with an impervious resin.
- Always ensure good ventilation when using Sikafloor®-29 PurCem® in a confined space, to prevent excessive ambient humidity.
- Freshly applied Sikafloor®-29 PurCem®, must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.
- Protect the substrate during application from condensation from pipes or any overhead leaks.
- Do not apply to cracked or unsound substrates.
- Always allow a minimum of 48 hours after product application prior to placing into service in proximity with food stuffs.
- Products of the Sikafloor® PurCem® product range are subject to discolouration when exposed to UV radiation. Extend depends on colour. There are no measurable losses of any properties when this occurs and it is a purely aesthetical matter. Products can be used outside provided the change in appearance is acceptable by the customer.
- In some slow curing conditions, soiling of the surface may occur when opened to foot traffic, even though mechanical properties have been achieved. It is advised to remove dirt using a dry mop or cloth. Avoid scrubbing with water for the first three days.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

Priming is required to install Sikafloor®-29 PurCem®. Sikafloor 160/161 or Sikadur 31/33 are acceptable primers for various different types of applications. Please see Application Information below for further details.

MIXING

Premix part A with a low speed electric stirrer and then add pigment and mix until uniform. Add part B and mix for 30 seconds. Make sure all pigment is uniformly distributed. Use a double paddle (axis) mixer and gradually add part C & D (aggregate) to the mixed resin. **DON'T DUMP!**

Allow part C & D to blend for further 2 minutes minimum, to ensure complete mixing and a uniform moist mix is obtained. During the operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once (parts A+P+B+C+D) to ensure complete mixing. Mix full units only.

Mixing tools

Use a low speed electric stirrer (300-400 rpm) for mixing parts A and B. For preparation of the mortar mix use a pan type revolving mixer.

APPLICATION

Priming:

Subject to the various applications, different epoxy primers can be used, For standard covers under 100mm in Height, Sikafloor 160/161 should be used.

For concrete kerbs and vertical renders, Sikadur 31/33 can be used, for vertical applications apply the Sikadur 31/33 by way of a 4mm V-Notch Trowel prior to the application of Sikafloor®-29 PurCem® the Thixotropic Nature of the Sikadur 31/33 Adhesives will greatly aid in the ability of the Sikafloor®-29 PurCem® to hold in place on vertical applications.

Application of Sikafloor®-29 PurCem®

Apply the mixed Sikafloor®-29 PurCem® onto the ready primed substrate and compact to the appropriate thickness, then finish the detailing profile with a coving trowel or steel float. Apply Sikafloor®-29 PurCem® while the primer is still tacky. If the primer becomes tack free, reapply the primer.

Top Coats:

Sikafloor®-29 PurCem® is fully servicable without top coats, however in order to provide a smoother and more colour consistent finish, 1-2 x Coats of Sikafloor 31 PurCem top Coat should be applied.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened/cured material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

will be supplied on request.

Product Data Sheet

Sikafloor®-29 PurCem®

April 2023, Version 05.01

020814020020000022

Sikafloor-29PurCem-en-AU-(04-2023)-5-1.pdf