

## PRODUCT DATA SHEET

# Nailbond® SuperGrip 30 Minute

## FAST CURING PREMIUM POLYURETHANE CONSTRUCTION ADHESIVE

## DESCRIPTION

A transparent polyurethane paste adhesive. Nailbond® SuperGrip 30 Minute is a versatile, ready to use, fast curing, general purpose construction adhesive.

## USES

Bonding of:

- Edge bonding of particle board flooring
- Timber & MDF
- Marble & stone
- Concrete
- Brick/blocks
- Glass
- Fibre cement
- Tiles
- Rubber
- Metals
- Aluminium

## CHARACTERISTICS / ADVANTAGES

- 100% waterproof (BS-EN204)
- Incredibly strong
- Bonds almost anything, including LOSP treated timber
- Non drip
- No shrinkage
- Cures in 30 minutes\*
- Interior and exterior use
- High temperature resistance (-30°C to +100°C)
- Cures transparent
- Does not stain

## PRODUCT INFORMATION

Composition	Transparent polyurethane paste
Packaging	310ml cartridges
Shelf life	Twelve (12) months from date of production when stored as stated.
Storage conditions	Store in original, unopened packaging in cool, dry conditions.
Colour	Translucent
Density	1.12g/cm <sup>3</sup>
Solid content by mass	100% approximately

## TECHNICAL INFORMATION

Service temperature	-30°C to +100°C
---------------------	-----------------

## APPLICATION INFORMATION

<b>Ambient air temperature</b>	+5°C to +35°C
<b>Open Time</b>	<b>Relocation Time:</b> Approximately 5-10 minutes depending on temperature and ventilation.
<b>Curing time</b>	Approximately 30 minutes, depending on temperature, moisture content of surfaces and adhesive thickness. Strength will increase over the next 24 hours.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

- One or both of the materials to be bonded must be porous.
- Gap filling capacity is limited.
- Gap-filling performance may be enhanced by a slight moistening of the substrate surfaces.
- A perfect fit of components is required for a watertight bond.
- Surfaces may be damp or slightly moist, but all free liquid water must be removed.
- Fastest bond time will be achieved with dry substrates. It is best practice to increase the clamp time when using damp materials.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

All surfaces must be clean and free from all dust, laitance, scale, rust, loose particles, grease and foreign matter.

### APPLICATION METHOD / TOOLS

#### GUN APPLICATION

- Cut end off cartridge nozzle at a 45° angle to give a 5-6 mm bead. Fit cartridge into a Sika gun.
- Apply adhesive thinly to one surface, or both surfaces if very porous or absorbent.
- Join surfaces within 5 minutes. A perfect fit is required for a watertight bond. Clamping or pressing will increase bond strength.
- Clamp time: 20-30 minutes at +15°C to +20°C. Clamp for longer if the temperature is below +10°C or sub-

Sika Australia Pty Limited  
ABN 12 001 342 329

#### CLEANING OF EQUIPMENT

Tel: 1300 22 33 48

Clean up with acetone or white spirit. Cured adhesive can only be removed mechanically.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.