

PRODUCT DATA SHEET

SikaWrap®-230 C

Woven unidirectional carbon fibre fabric, designed for structural strengthening applications as part of the Sika® strengthening system.

DESCRIPTION

SikaWrap®-230 C is a unidirectional woven carbon fibre fabric with mid-range strength, designed for installation using the dry or wet application process.

USES

SikaWrap®-230 C may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Replacing missing steel reinforcement
- Increasing the strength and ductility of columns
- Increasing the loading capacity of structural elements
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards

CHARACTERISTICS / ADVANTAGES

- Manufactured with heat-set weft fibres to keep the fabric stable
- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating to different surface planes and geometry (beams, columns, chimneys, piles, walls, soffits, silos etc.)
- Available in different widths for optimum utilisation
- Low density for minimum additional weight
- Extremely cost effective in comparison to traditional strengthening techniques

APPROVALS / CERTIFICATES

- Poland: Technical Approval ITB AT-15-5604/2011: Zestaw wyrobów Sika CarboDur do wzmacniania i napraw konstrukcji betonowych
- Poland: Technical Approval IBDiM Nr AT/2008-03-0336/1 „Płaskowniki, pręty, kształtki i maty kompozytowe do wzmacniania betonu o nazwie handlowej: Zestaw materiałów Sika CarboDur® do wzmacniania konstrukcji obiektów mostowych
- France: Avis Technique N° 3/16-875 (annule et remplace N° 3/10-669) Sika® CarboDur®, SikaWrap®
- USA: ACI 440.2R-08, Guide for the Design and construction of Externally Bonded FRP Systems for strengthening concrete structures, July 2008
- UK: Concrete Society Technical Report No. 55, Design guidance for strengthening concrete structures using fibre composite material, 2012.

PRODUCT INFORMATION

Construction	Fibre orientation	0° (longitudinal, unidirectional)
	Warp	Black carbon fibres 99 %
	Weft	White thermoplastic heat-set fibres 1 %
Fibre type	Selected mid-range strength carbon fibres	

Packaging	Fabric length per roll	Fabric width
	1 rolls in a cardboard box (50m ² per roll)	≥ 100 m
Shelf life	24 months from date of production	
Storage conditions	Store in undamaged, original sealed packaging, in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight.	
Dry fibre density	1.82 g/cm ³	
Dry fibre thickness	0.129 mm (based on fibre content)	
Mass per area	235 g/m ² ±10 g/m ² (carbon fibres only)	
Dry fibre tensile strength	4 000 N/mm ²	(ISO 10618)
Dry fibre modulus of elasticity in tension	230 000 N/mm ²	(ISO 10618)
Dry fibre elongation at break	1.7 %	(ISO 10618)

TECHNICAL INFORMATION

Design nominal thickness	0.129 mm		
Design nominal cross section	129 mm ² per m width		
Laminate tensile strength	Average	Characteristic	(EN 2561*)
	3 500 N/mm ²	3 200 N/mm ²	(ASTM D 3039*)
Laminate modulus of elasticity in tension	Average	Characteristic	(EN 2561*)
	225 kN/mm ²	220 kN/mm ²	
	Average	Characteristic	(ASTM D 3039*)
	220 kN/mm ²	210 kN/mm ²	
* modification: sample with 50 mm Values in the longitudinal direction of the fibres Single layer, minimum 27 samples per test series			
Laminate elongation at break in tension	1.56 %		(based on EN 2561)
	1.59 %		(based on ASTM D 3039)
Tensile resistance	Average	Characteristic	(based on EN 2561)
	452 kN/m	413 kN/m	(based on ASTM D 3039)
Tensile stiffness	Average	Characteristic	(based on EN 2561)
	29.0 MN/m	28.4 MN/m	
	29.0 kN/m per ‰ elongation	28.4 kN/m per ‰ elongation	
	Average	Characteristic	(based on ASTM D 3039)
	28.4 MN/m	27.1 MN/m	
	28.4 kN/m per ‰ elongation	27.1 kN/m per ‰ elongation	

SYSTEM INFORMATION

System structure

The system build-up and configuration as described must be fully complied with and may not be changed.

Concrete substrate adhesive primer Sikadur®-330

Impregnating / laminating resin Sikadur®-330 or Sikadur®-300

Structural strengthening fabric SikaWrap®-230 C

For detailed information on Sikadur®-330, together with the resin and fabric application details, please refer to the Sikadur®-330 Product Data Sheet and the relevant Method Statement.

APPLICATION INFORMATION

Consumption

Dry application with Sikadur®-330

First layer including priming layer 0.8–1.2 kg/m²

Following layers 0.7 kg/m²

Wet application with Sikadur®-300, primer Sikadur®-330

Primer layer 0.4–0.6 kg/m²

Fabric layers 0.6 kg/m²

Please also refer to the relevant Method Statement for further information.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Method Statements

Ref. 850 41 02: SikaWrap® manual dry application

Ref. 850 41 03: SikaWrap® manual wet application

Ref. 850 41 04: SikaWrap® machine wet application

IMPORTANT CONSIDERATIONS

- SikaWrap®-230 C shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-230 C fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not exchange system components.
- SikaWrap®-230 C can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional UV light protection in exposed areas use Sikagard®-550 W Elastic, Sikagard® ElastoColor-675 W or Sikagard®-680 S.
- Please refer to the relevant Method Statement of SikaWrap® for further information, guidelines and limitations.

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Minimum substrate pull-off strength: 1.0 N/mm² or as specified in the strengthening design.

Please also refer to the relevant Method Statement for further information.

SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface. Please also refer to the relevant Method Statement for further information.

APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric.

SikaWrap®-230 C is applied using the dry or wet application process.

Please refer to the relevant Method Statement for de-

tails on the impregnating / laminating procedure.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

SikaWrap-230C-en-AU-(04-2023)-2-2.pdf

Product Data Sheet

SikaWrap®-230 C

April 2023, Version 02.02

020206020010000025

