

## PRODUCT DATA SHEET

SikaCeram<sup>®</sup>-880 Easy Epoxy

Easy to use epoxy tile grout and adhesive.

## DESCRIPTION

SikaCeram<sup>®</sup>-880 Easy Epoxy is a two-part, easy to use, coloured epoxy-based tile grout and adhesive. It is suitable for floor and wall application.

## USES

SikaCeram<sup>®</sup>-880 Easy Epoxy is used for bonding and grouting of the following types of tiles:

- Ceramic and porcelain tiles
- Glass mosaic

SikaCeram<sup>®</sup>-880 Easy Epoxy is used for bonding and grouting tiles for the following applications:

- Seawater pools
- Swimming pools
- Thermal pools
- Turkish baths
- Private and public bathrooms
- Commercial, industrial, or residential kitchens
- Dairies
- Tanneries
- Paper mills
- Laboratories
- Slaughterhouses

SikaCeram<sup>®</sup>-880 Easy Epoxy is used for interior and exterior applications.

Please note:

- The Product may only be used by experienced professionals.
- Do not use for any other applications that are not explicitly described in this Product Data Sheet.

## FEATURES

- Grout joint range: 1 to 20 mm
- Very good resistance to specific chemicals
- Good resistance to staining
- Easy to clean
- Highly thixotropic for tiling and grouting on floor and wall
- Impermeable to water and water vapour
- High abrasion resistance
- Very good workability
- Very good UV stability

## SUSTAINABILITY

- VOC emission classification GEV Emission EC1<sup>plus</sup>

## CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 12004:2007+A1:2012 Adhesives for tiles — Reactive resin adhesives — All internal and external tiling

## PRODUCT INFORMATION

Composition	Epoxy resin, aggregates and special additives
Packaging	5 kg containers (Part A+B)
Colour	White, Silver Grey, Grey, Anthracite, & Platinum Grey
Shelf life	24 months from date of production

<b>Storage conditions</b>	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 0 °C and +30 °C. Always refer to the packaging.		
<b>Product declaration</b>	Adhesive for ceramic tiles	Class: R2 T	AS ISO 13007
	Grout for tiles	Class: RG	AS ISO 13007
<b>Appearance</b>	Part A: Viscous liquid, Part B: Coloured paste		

## TECHNICAL INFORMATION

Abrasion resistance	≤ 250 mm <sup>3</sup>		(EN 12808-2)
Compressive strength	≥ 45 MPa		(EN 12808-3)
Flexural-strength	≥ 30 MPa		(EN 12808-3)
Shrinkage	≤ 1.5 mm/m		(EN 12808-4)
Tensile adhesion strength	Initial	≥ 2 MPa	AS ISO 13007
	Water immersion	≥ 2 MPa	
	Thermal shock	≥ 2 MPa	
Chemical resistance	Resistant to many chemicals. Contact Sika Technical Services for additional information.		
Temperature resistance	Maximum	+80 °C	
	Minimum	-20 °C	
Skid / slip resistance	≤ 0.5 mm		(EN 12004-2)
Joint width	Maximum	20 mm	
	Minimum	1 mm	
Water absorption	After 240 mm - ≤ 0.1 g		(EN 12808-5)

## APPLICATION INFORMATION

<b>Mixing ratio</b>	Part A+B	4.01 kg base component + 0.99 kg hardener component
<b>Consumption</b>	Approximately 1.6 kg/m <sup>2</sup> and mm layer thickness	
	TILE LAYING	
	<b>Notch size</b>	<b>Consumption</b>
	4 mm	1.9 kg/m <sup>2</sup>
	6 mm	2.3 kg/m <sup>2</sup>
	8 mm	3.2 kg/m <sup>2</sup>
	10 mm	3.8 kg/m <sup>2</sup>
	GROUTING	
	<b>Notch size</b>	<b>Consumption</b>
	Medium mosaic 5 × 5 cm (3 mm joint width, 5 mm joint depth)	1.0 kg/m <sup>2</sup>
	Tiles 20 × 20 cm (5 mm joint width, 8 mm joint depth)	0.7 kg/m <sup>2</sup>
	Fully vitrified tiles 30 × 60 cm (4 mm joint width, 8 mm joint depth)	0.3 kg/m <sup>2</sup>
<b>Layer thickness</b>	Minimum adhesive bed thickness	1 mm

<b>Material temperature</b>	Maximum	+25 °C
	Minimum	+5 °C
<b>Substrate temperature</b>	Maximum	+25 °C
	Minimum	+10 °C
<b>Substrate moisture content</b>	Cementitious substrates	Calcium carbide method (CM-method) ≤ 4 %
<b>Pot Life</b>	At +20 °C	45 min
<b>Open Time</b>	60 minutes	
<b>Curing time</b>	<b>TILING</b>	
	Waiting time before grouting on the wall	4 hours
	Waiting time before grouting on the floor	16 hours
	<b>GROUTED FLOOR COVERING</b>	
	Walkable after	16 hours
	Can be exposed to water or chemicals after	3 to 7 days
<b>Waiting time</b>	Emulsifiable/rewashable	10–60 minutes

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### EQUIPMENT

#### MIXING EQUIPMENT

- Electric single-paddle mixer (up to 300 rpm) with spiral paddle

#### APPLICATION EQUIPMENT

- Notched trowel
- Trowel
- Rubber float
- Sponge float
- Soft cloth
- Grout finishing tool

### SUBSTRATE PREPARATION

#### TILING

Suitable substrates include the following materials:

- Cementitious materials
- Gypsum and cement-based substrates
- Paint coating

- Tiles
- Metal
- Glass fibre-reinforced plastic

For other substrate types, contact Sika Technical Services.

#### IMPORTANT

##### Carry out equipment trials

Carry out equipment trials to make sure the Product can be mixed satisfactorily before full project application.

The following conditions regarding substrate quality must be fulfilled or appropriate measures must be taken.

- Cementitious substrates must be sufficiently cured and dried (between 2 to 6 weeks).
- All substrates must possess structural stability to bear the weight of the new tiling while providing a secure and firm base.
- Surfaces must be dry and clean, free of loose or friable particles and contaminants such as dust, dirt, oil, wax polish, grease, cement laitance, or efflorescence.
- Prepare substrates mechanically using techniques such as sanding and scraping to remove all traces of any materials that could reduce the product's adhesion to the substrate. Remove all dust, loose and friable material from the application surface with industrial vacuuming equipment.
- Smooth surfaces must be roughened lightly to improve adhesion.
- When laying tiles on non-absorbent or substrates with limited absorbency, such as existing tiles or painted surfaces, ensure these surfaces are stable, firmly bonded, and securely in place. Afterwards, use suitable degreasing or descaling products to clean the surface thoroughly and completely.
- For tiling in constantly damp or wet rooms, a suitable

Sika® waterproofing product or system must be applied to the substrate before tiling.

#### GROUTING

- All surfaces must be clean, dry and free of grease.
- Ensure the joint does not contain excess tile adhesive.

#### MIXING

SikaCeram®-880 Easy Epoxy is a reactive product. It sets from a chemical reaction between the two parts, A and B. These parts must be thoroughly mixed at the correct mixing ratio. Mix full units only.

1. Mix part A (the resin component) briefly using an electric single paddle mixer with a spiral paddle.
2. Add part B (hardener) to part A and mix both parts continuously for 3 minutes until the mixture achieves a uniform colour.
3. Transfer mixed material to a clean bucket and mix again thoroughly.

#### APPLICATION

##### IMPORTANT

**Risk of cracking due to application in direct sun or strong winds**

- Do not apply the Product in hot direct sun, strong winds or both.

##### IMPORTANT

##### Absorbency of natural stone

Staining from plasticiser migration may occur when used on natural stone.

- Conduct a test prior to application

#### TILE GROUTING

SikaCeram®-880 Easy Epoxy is applied using an appropriate rubber float.

##### Preconditions

Observe the tile adhesive curing time before starting to grout.

1. Completely fill the joints and compact them uniformly.
2. Using the same float, remove excess grout from the tile surfaces, moving the tool diagonally across the joints.

#### TILE CLEANING

##### IMPORTANT

##### Leaving the surface too long before cleaning

Epoxy haze caused during application will be difficult to safely remove if the SikaCeram®-880 Easy Epoxy is left too long before cleaning.

1. At +20 °C the initial, emulsifying clean can be given 10–45 minutes after finishing the grouting.
2. At +20 °C, the surface can be given a second clean, using more water, up to 60 minutes after mixing the Product.
3. Higher ambient temperatures will reduce this period and lower ambient temperatures will extend it.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

#### Preconditions

The grout has set sufficiently to avoid it being removed from the joint during cleaning.

1. For an initial, emulsifying clean, use a small amount of clean water and a sponge float.
2. Rub the tiles in a circular motion to remove excess material. Rinse the sponge frequently.
3. For the second clean, wash the surface with a sponge float in diagonal movements. Add SikaCeram®-960 Epoxy Finish to the wash water, diluted 1 : 100.
4. **IMPORTANT** Rinse the sponge and change the wash water frequently. Remove any smears or remaining haze.
5. On the same day, check if the surface is clean as soon as it has dried. Repeat the cleaning process if necessary.
6. When the grout has cured the next day, use SikaCeram®-960 Epoxy Finish diluted 1 : 100 in clean water to remove any remaining haze.

#### CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

#### LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

#### LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Product Data Sheet

SikaCeram®-880 Easy Epoxy

December 2025, Version 02.01

021720301000000097

SikaCeram-880EasyEpoxy-en-AU-(12-2025)-2-1.pdf