

PRODUCT DATA SHEET

Sikagard[®]-6060 S

Sprayable, bitumen-based underbody coating in aerosol can

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	Bitumen solution
Colour (CQP001-1)	Black
Cure mechanism	Air-drying
Solid content	33 %
Application temperature	15 – 25 °C
Film thickness	wet 400 µm dry 150 µm
Tack free time (CQP 019-1)	75 minutes ^A
Drying time	2.5 h ^A
Service temperature	-25 – 80 °C
Shelf life	24 months ^B

CQP = Corporate Quality Procedure

^{A)} 23 °C / 50 % r. h.^{B)} storage between 5 °C and 25 °C
DESCRIPTION

Sikagard[®]-6060 S is a fast-drying, bitumen-based, quick-repair protective coating in an aerosol can with very good rust-proofing and sound deadening properties. It is suitable for an effective vehicle underbody protection. Sikagard[®]-6060 S can be sprayed haze free without any cob-webbing and does not drip. Sikagard[®]-6060 S shows good adhesion on different paints, metal primers, metals and PVC without any pre-treatment. A tough coating remains after drying, protecting metal from corrosion.

PRODUCT BENEFITS

- Equipment independent (aerosol). Easy to use.
- Outstanding application properties (no running or dripping)
- Good adhesion performance to a wide variety of substrates
- Excellent acoustic and damping properties
- fast drying
- Road salt resistant
- High solid content

AREAS OF APPLICATION

Sikagard[®]-6060 S is a spray-applied, anti-corrosion coating for quick repairs of non-visible areas such as wheel arches and underbody parts of vehicles that do not need to be over painted.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed to ensure adhesion and material compatibility.

CHEMICAL RESISTANCE

Sikagard®-6060 S is resistant against water, seawater, salt spray, bases and acids. The above information is offered for general guidance only. Advice on specific applications will be given on request.

METHOD OF APPLICATION

Surface preparation

Surfaces must be clean, dry and free of rust, dust and grease. Bare metal substrates must be pretreated to enhance corrosion resistance (e.g. uncoated steel, etc).

Application

Shake can approx. 40 times before use. Cover adjacent surfaces prior the spray process. Spray at room temperature and from a distance of approx. 25 cm in an grid motion to build up a continuous coat.

Sikagard®-6060 S can be applied without dripping. If a thick layer is required, let layers dry in between. Hold the can in an upright position and do not spray on parts of the brake, engine or exhaust system.

After use, invert can and spray in short bursts to clear nozzle.

Removal

Uncured Sikagard®-6060 S can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once dried, the material can only be removed mechanically. Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water. Do not use solvents on skin.

Overpainting

Sikagard®-6060 S cannot be overpainted.

FURTHER INFORMATION

Copies of the following publication is available on request:

- Safety Data Sheet

PACKAGING INFORMATION

Aerosol can	500 ml
-------------	--------

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PRODUCT DATA SHEET

Sikagard®-6060 S
Version 02.01 (03 - 2023), en_AU
013913010603001100

Sika Australia Pty Limited

ABN 12 001 342 329
aus.sika.com
Tel: 1300 22 33 48

